University of Dundee

Geomicrobiology of the built environment

Gadd, Geoffrey Michael

Published in:
Nature Microbiology

DOI:
[10.1038/nmicrobiol.2016.275](https://doi.org/10.1038/nmicrobiol.2016.275)

Publication date:
2017

Document Version
Peer reviewed version

[Link to publication in Discovery Research Portal](#)

Citation for published version (APA):

Gadd, G. M. (2017). Geomicrobiology of the built environment. *Nature Microbiology*, 2, 1-9. [16275].
<https://doi.org/10.1038/nmicrobiol.2016.275>

General rights

Copyright and moral rights for the publications made accessible in Discovery Research Portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from Discovery Research Portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain.
- You may freely distribute the URL identifying the publication in the public portal.

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Geomicrobiology of the built environment

Geoffrey Michael Gadd^{1,2*}

¹*Geomicrobiology Group, School of Life Sciences, University of Dundee, Dundee, DD1 5EH, Scotland, United Kingdom*

²*Laboratory of Environmental Pollution and Bioremediation, Xinjiang Institute of Ecology and Geography, Chinese Academy of Sciences, Urumqi 830011, People's Republic of China*

Correspondence

Professor G.M. Gadd, Geomicrobiology Group, School of Life Sciences, University of Dundee, Dundee, DD1 5EH, Scotland, United Kingdom.

Tel.: +44 1382 384767; E-mail: g.m.gadd@dundee.ac.uk

Running title: Geomicrobiology of the built environment

Keywords: Geomicrobiology; Geomycology; Built Environment; Cultural Heritage; Biodeterioration; Biocorrosion

Abstract

Microbial colonization and growth can have significant effects in the built environment, resulting in a range of effects from discolouration and staining to biodeterioration and decay. In some cases, formation of biofilms, crusts and patinas may confer bioprotection of the substrate. This perspective aims to discuss how geomicrobial transformations in the natural environment - particularly involving rocks, minerals, metals and organic matter - may be applied to understand similar processes occurring on fabricated human structures. However, the built environment may offer further strictures as well as benefits for microbial activity and these should be taken into consideration when considering analogy with natural processes, especially when linking observations of microbial biodiversity to the more obvious manifestations of microbial attack.

Introduction

Geomicrobiology is concerned with the influence of microorganisms on processes related to geology^{1,2}, which includes bioweathering of rocks and minerals, metal and radionuclide transformations, mineral deposition, soil formation, and biogeochemical cycling of the elements. Bioweathering is the biotic erosion and decay of rocks, stone and minerals, and is mediated through physical and biochemical mechanisms³⁻⁶. Biodegradation is a term applied to organic substrates that may provide a source of carbon and energy for the degrading microorganisms⁷, but may be important in enhancing bioweathering by chemoorganotrophs. Biofouling results when surface microbial growth results in formation of biofilms, slimes and discolouration, but this does not necessarily result in bioweathering of the substrate⁷.

As many geomicrobial processes are concerned with interactions between organisms and abiotic substrates, there can be significant consequences for human-built structures derived from rocks, minerals, and metals. In addition, the major degradative properties of microorganisms, primarily bacteria and fungi, on natural and synthetic carbon-containing materials such as wood and plastics ensure that both organic and inorganic components of

human-built structures are subject to microbial influence. An understanding of geomicrobiology can assist interpretation of the colonization, biodeterioration and decay of human-built structures as well as provide information on preventative or restorative treatments. In this article, human-made structures include the built environment, nuclear repositories, industrial plant, and cultural heritage (see Box 1). The objective of this perspective is to highlight microbial roles in affecting the appearance and structure of the built environment, and to draw parallels, where possible, with geomicrobial processes occurring in the natural environment.

Sequencing-based surveys of the built environment

Biodiversity studies have shown that architectural design influences the indoor built environment microbiome^{8,9} with indoor bacteria mostly comprising human-associated species and the fungal microbiome originating from outdoors⁸⁻¹³. Most studies are concerned with bacteria and human health consequences^{12,14,15} rather than biodeterioration. Biodiversity studies of stone-inhabiting organisms on buildings and monuments also concentrate on bacteria¹⁶, and few are linked with geomicrobiology. Although the number of eukaryotic studies is limited, algal and fungal communities on stone tend to exhibit low biodiversity compared to natural environments, with fungal communities being richer and heterogeneous¹⁶. Several taxa identified appear rare and of low ecological importance¹⁶, while differences in the efficiency of DNA extraction methods can be extreme for microbes on building materials¹⁷. Although sequencing studies can provide community comparisons between sites and geographic regions^{13,18}, and the relative dominance of different species¹⁸⁻²⁰, there is little understanding of function or ecological interactions in a geomicrobial context¹¹. Some sophisticated studies add little to earlier findings using traditional methods¹¹. There are also several technological artefacts and innate biological traits that bias relative quantification of abundance¹⁹, although a combination of electron microscopy with metabolomic and genomic techniques allowed some linkage of phylogenetic data with metabolic profiles²¹. However, such studies describe functional potential, and it is difficult to definitively link phylogeny and function^{20,22}. It is

clear that culture-based methods are still essential for studying geomicrobial transformations of human-made structures.

Microorganisms from all the major groups, Bacteria, Archaea and Eukarya, can operate as geomicrobial agents in a variety of contexts depending on their geoactive properties which affect organic and inorganic substrates^{1-3,23,24}. This simple fact is often unappreciated in geomicrobiology where the metabolic diversity of archaea and bacteria ensures the majority of scientific attention is given to these prokaryotes to the exclusion of eukaryotes^{25,26}. For example, fungi are considered to be the most important colonizers on, e.g. stone, mortar and plaster^{6,27,28}, and participate in many important environmental processes including elemental cycling, rock and mineral transformations, and soil formation and structure^{24,29-31}. Likewise, lichens, a fungal growth form³², are also significant biodeteriorative agents of stone monuments, buildings, cements and mortars³³⁻³⁵. Further complexity of bioweathering microbial communities arises from bacterial associations with lichens which, so far, are poorly understood³⁶. Algae have major influences on global carbon cycling³⁷ and are ubiquitous in the built environment. Given the presence of natural materials in human-made structures, these biases are likely to carry over to studies of the built environment. This lack of attention is ironic as fungi and algae are responsible for some of the most obvious visible manifestations of microbial colonization of human-built structures.

Rock and mineral-based structures in the built environment

Bioweathering mechanisms affecting rock and mineral-based structures are identical to those in the terrestrial environment that ultimately lead to mineral soil formation^{1,29,30}. In the long term, therefore, this can be considered to be the ultimate fate of rock and mineral-based human-built structures, including buildings and cultural heritage, with some added complicatory factors which may accelerate or inhibit bioweathering and biodegradation. These include climatic factors and the presence of additional structural materials, such as wood, plastic and metals, atmospheric pollution, and protective treatments.

Factors affecting microbial colonization

Stone-inhabiting microbes may grow on the surface (epilithic), in crevices and fissures (chasmolithic), or may penetrate some millimetres or even centimetres into the rock pore system (endolithic) gaining protection from environmental extremes³⁸. Many organisms scavenge nutrients from the atmosphere and rainwater, and also use organic and inorganic residues on surfaces or within cracks and fissures, waste products of other microbes, decaying plants and insects, dust particles, aerosols and animal faeces as nutrient sources^{27,39}. Exterior stone surfaces are usually regarded as an extreme habitat because of UV radiation, temperature and moisture variations, and lack of available nutrients⁴⁰. Some fungal groups exhibit microcolonial or yeast-like growth forms that are effective in providing protection from heat and desiccation²³. These may prevail under harsh conditions, and appear as black spots due to possession of UV-protective melanins^{5,23,41}. Hyphae may penetrate the substratum under the colonies, while surface biomineralization may lead to the formation of robust varnish-like coatings^{23,42}. Lichen cover may also offer bioprotection^{5,43,44}. The accelerated deterioration that may occur if outer layers of buildings and monuments are removed for cleaning by physical and chemical methods is well documented^{4,5,45}. Additionally, atmosphere-exposed microbial communities or “subaerial biofilms”^{15,46} may produce protective exopolymeric substances (EPS), also capable of metal complexation, which aid colonization and survival.

The pore spaces in rocks, the endolithic environment, can also host photosynthesis-based communities that are often thought to be among the simplest ecosystems known⁴⁷. Although this may be true in some instances, it is clear that some rock communities show considerable biodiversity^{23,39,48-51}. This may be especially true of the built environment where atmospheric and anthropogenic influences may enhance colonization and growth^{4,45,52} and where clear separation of endolithic and epilithic communities and their effects on the substrate are difficult to separate²⁸.

Microbial diversity on rock-based structures

Many rock-based structures support thriving multi-species communities that are likely to be determined by the nature of the urban environment and anthropogenic

influence^{39,45,52-54}. Biofilms, including cyanobacteria, green algae and fungi, are particularly evident in altering the appearance of stone structures^{7,55}, with fungi considered to be the most important chemoorganotrophs^{56,57}.

All major metabolic groups of microorganisms can be found including chemolithotrophs, chemoorganotrophs and phototrophs and biodeteriorative effects can be detected even in early stages of stone exposure²³. Although it is usually thought that phototrophs are primary colonizers³⁸, it is clear that chemoorganotrophs can also be primary colonizers, achieving dominance in the absence or presence of phototrophs^{4,23,58}, especially where there is atmospheric organic pollution which may significantly accelerate stone decay^{4,5}. Atmospheric gases, aerosols, pollutants and particulates can be accumulated in biofilms and serve as nutrient sources as well as inoculum^{4,5,23}. Several bacteria and fungi can utilize organic pollutants²³ and in polluted urban environments, hydrocarbon-utilizers and sulfur-oxidizers may be enriched⁵⁹. Organic components in the rock substrate or atmosphere also encourage chemoorganotrophic development, which in turn leads to further organic enrichment of the system through biomass production, exudation and exopolymer synthesis⁴. Which particular microbial community dominates can depend on the substrate, the atmosphere, and abiotic stresses^{5,23}. Highly deteriorated stone surfaces provide appropriate conditions (a 'proto-soil') for further colonization by mosses, ferns and higher plants^{6,7}.

Mechanisms of rock/mineral bioweathering

The susceptibility of stone and mineral-based material to bioweathering is influenced by chemical and mineralogical composition, physical form, and geological origin^{4,60,61}. The presence of weatherable minerals in stone such as feldspars and clays may provide points of weakness and significantly increase susceptibility to attack⁴. Typical mechanisms of microbial weathering involve physical and biochemical destruction. Physical mechanisms of bioweathering (Figure 1) include penetration by filamentous microorganisms (e.g. certain actinobacteria, cyanobacteria, algae, fungi) along points of weakness, or direct tunnelling or boring, especially in weakened or porous substrata^{38,62-67}. Many cyanobacteria, not necessarily filamentous, have also been shown to have a boring ability⁶⁶. Organisms that actively bore ("euendoliths") widely occur in cyanobacteria, red and green algae and fungi⁶⁶.

Biofilms cause weakening of the mineral lattice through wetting and drying cycles and subsequent expansion and contraction^{4,23}. Lichens cause mechanical damage due to penetration of their root-like anchoring structures (“rhizines”), composed of fungal filaments, and expansion/contraction of the vegetative body (“thallus”) on wetting/drying, which can lift grains of stone from the surface^{68,69}. Such effects as well as thallus removal by animals, and wind, rain, hail, sleet and snow can lead to visible mechanical damage in less than 10 years^{68,70}. Other physical effects on substrate integrity can be due to cell turgor pressure, and exopolysaccharide and/or secondary mineral formation⁷¹. The production of efflorescences (‘salting’) involves secondary minerals produced through reaction of anions from excreted acids with cations from the stone. Such secondary mineral formation can cause blistering, scaling, granular disintegration, and flaking or “spalling” of outer layers. This may often be a major mechanism of stone decay^{5,72}.

Biochemical weathering of rock and mineral substrates (Figure 1) can occur through excretion of, e.g., H^+ , CO_2 , organic and inorganic acids, siderophores, and other metabolites, and can occur in conjunction with biophysical mechanisms^{2,71,73,74}. This can result in pitting, etching and complete dissolution. Sulfur and sulfide-oxidizing bacteria, e.g. *Acidithiobacillus* spp., are well known for their bioleaching and deteriorative actions on sulfidic-ore substrates as well as concrete, bricks and mortar⁵³. Acidithiobacilli and sulfate-reducing bacteria (SRB) can be very important bacteria in biodeterioration of concrete⁶¹. Many bacteria, especially anaerobes, can use alternative electron acceptors for respiration, e.g. NO_3^- , SO_4^{2-} , Fe(III), and Mn(IV)⁷⁵. The reduction (or oxidation) of such components in minerals can result in instability and dissolution^{1,36}. Microbial attack on concrete appears to be mainly mediated by acidity (H^+ , inorganic and organic acids) and the production of hydrophilic slimes as well as biophysical disruption^{3,6,61,76,77}. In cementitious-bound concrete, the calcium oxide/hydroxide/silicate can react with CO_2 to form $CaCO_3$ (“carbonatization”). This leads to a fall in pH to around pH 8.5 which is more amenable for microbial growth. This growth in turn leads to enhanced acid production and further pH decreases to the point at which iron/steel reinforcements can become more susceptible to corrosion³. It is conceivable that over the long term, microbial biodeterioration of concrete and biocorrosion of metals will compromise current methods of radionuclide containment and storage.

Some organic metabolites effect dissolution by complexation of constituent metals and removal from the mineral in a mobile form. Biogenic organic acids are more effective in mineral dissolution than inorganic acids and are one of the most damaging agents affecting stone^{1,4}. This underlines the importance of fungi including lichens^{24,68,70,78}. Of the suite of organic acids produced by fungi, oxalate is of major significance through metal complexation and dissolution effects⁷⁸ as well as causing physical damage by formation of secondary metal oxalate biominerals expanding in pores and fissures^{70,79}. Likewise, lichens produce 'lichen acids', (principally oxalic acid), which cause damage at the stone/lichen interface. Lichen thalli may accumulate 1–50% metal oxalates (the main secondary crystalline products of lichen bioweathering), depending on the substrate^{34,63}.

The opposing phenomenon of biomineralization, i.e. the biologically-mediated formation of minerals, is also an important component of bioweathering. This can result from, e.g. oxidation or reduction of a metal species, and metabolite excretion. Soluble Mn(II) may be oxidized by certain bacteria and fungi forming black Mn oxides, a common component of black patinas on stone⁴². Metabolites include CO₂ that can precipitate carbonates; excreted oxalate can precipitate many metal oxalates^{2,24,70}. The release of metals in mobile forms from dissolution mechanisms can therefore result in various secondary mineral precipitates depending on the physico-chemical composition of the microenvironment, and these include carbonates, phosphates, sulfides and oxalates^{1,2}. Such formations may contribute to physical disruption, staining and discolouration of rock and mineral surfaces, frescoes and wall paintings^{41,80} (Figure 2).

Microbial biodegradation of other building materials

Brick, mortar, plaster, gypsum, grouting, glass, metals, ceramics, wood, plastic and other materials and masonry components are all subject to microbial attack^{4,7,45,52,81}.

Metal substrates can be subject to biocorrosion, which accounts for ~20% of all metal corrosion⁵. Most biocorrosion studies on iron, copper, and aluminium and their alloys have concentrated on pure and mixed bacterial cultures⁸². The main microbes associated with metal biocorrosion are sulfate-reducing bacteria (SRB), sulfur-, iron- and manganese-oxidizing bacteria, and general species of bacteria, algae and fungi secreting organic acids

and slime, often in complex biofilm communities⁸²⁻⁸⁴ (Figure 1). Mechanisms of corrosion are complicated and include depolarization of metals, biomineral formation, complexation by exopolymeric substances (EPS), H₂ embrittlement, acidic attack and electron shuttling⁸³ often resulting in pitting⁵. Apart from iron removal from iron and steel, SRB-mediated SO₄²⁻ reduction can lead to precipitation of FeS and blackening of metal surfaces. Bird faeces were proposed to provide a phosphate source for biotransformation of lead sheeting leading to pyromorphite formation⁸⁴. Conversely, sulfur-oxidizers such as *Acidithiobacillus* spp. oxidize sulfur compounds generating sulfuric acid, while nitrifying bacteria produce nitric acid³⁻⁵; both acids attack metals, alloys and concrete, and can cause considerable damage³. Since alternation and stratification of aerobic and anaerobic conditions is common in natural habitats⁸⁵ and in biofilms^{82,86}, the processes of sulfate reduction or oxidation can occur continuously resulting in significant deterioration⁸³. Microbial exopolymers and organic acids, including oxalate, are also involved in biocorrosion by metal complexation as well as acid effects^{83,87}. Such biocorrosion may be enhanced by the proximity of an organic substrate, e.g. wood, acting as a reservoir of biodeteriorative microbes⁸⁷. Fungal organic acids have been shown to corrode fuel tanks where hydrocarbon-utilizing fungi can grow at water-fuel interfaces⁸³.

Oxalic acid is implicated in lichen biodeterioration of asbestos roofing material, which attacks the cement matrix⁸⁸. Lichen cover on asbestos may offer some “bioprotection” in stabilizing the surface and preventing asbestos detachment and dispersal^{88,89}. Similarly, copper(II) oxalate [Cu(C₂O₄).xH₂O] has been found in patinas on copper metal⁹⁰. Some of these outer formations incorporating oxalate are very stable and may also provide bioprotection from atmospheric weathering^{5,43,68,91}. Biodeterioration of ceramic roof tiles by lichens has also been identified as being caused by oxalic acid excretion⁹².

Glass is a ceramic material derived from silicate. All microbial groups may be involved in biodeterioration causing etching, loss of opacity and blackening, with redox transformations of, e.g. Fe, S and Mn, also causing discolouration and deterioration⁵. Medieval stained glass often shows corrosion, patina development, and mineral crust growth arising from complex microbial communities, including bacteria, fungi and lichens⁹³.

Biofouling, discolouration and staining

Discolouration and staining of human structures can be aesthetically unappealing and also reflect underlying bioweathering and microbial metal and mineral transformations. Such “biofouling”, often by microbial biofilms, may reflect the presence of photosynthetic pigments (cyanobacteria, algae - “greening”)^{45,94} or melanins and related substances (“blackening”) produced by many surface-inhabiting fungi^{4,27,95}. Biofilms may also trap dust, carbonaceous and other atmospheric particulates due to the presence of EPS⁹⁶. These factors as well as mineralogical changes can all contribute to discolouration and the formation of patinas and crusts^{4,5}. Mn(II) oxidation leads to black Mn(IV) oxide formation⁴². Rust-red or orange colours may be associated with iron oxidation¹. Biofouling also promotes biodeterioration by shrinking or expansion and moisture retention⁴.

Fungi are the principal deteriorating microbiota on painted surfaces in the built environment through colonization and biodegradation of organic components⁹⁷. Many paint-degrading fungi are black pigmented leading to extensive discolouration of affected surfaces.

The internal environment

Outer environments clearly cannot be controlled and microbial colonization, bioweathering and biodeterioration are markedly influenced by climate and location⁵. Indoor environments are strongly influenced by human occupancy and associated activities⁹⁸, but can be controlled, particularly regarding lighting, heating, humidity and ventilation. Where these factors are not controlled, especially moisture⁸¹, then biodegradation and biodeterioration of paper, wood, plaster and other structural components may be significant^{5,81}. This is particularly important in housing where extensive internal biodeterioration by bacteria and fungi can be a health hazard^{15,99}, and for cultural heritage where artwork, library, museum and other collections may be permanently affected or destroyed^{28,100} (Figure 1). Surface water is believed to be a prominent factor in influencing microbial changes⁸¹. The most important wood degraders are fungi such as various white-rot, brown-rot and soft-rot species, requiring an adequate wood moisture content to be effective⁵. Modern and ancient paper can contain large amounts of calcium carbonate¹⁰¹, as

well as metals arising from impurities, inks and pigments¹⁰⁰. Fungal biodeterioration can result in extensive calcium oxalate precipitation¹⁰¹. Microbial activity and metal-mineral transformations in paper can also result in the formation of reddish or brown staining termed “foxing”⁵. A given indoor microbiome can also be strongly influenced by architectural design^{8,9}. Further, variations in design and the use of differing building components around the world must also affect colonization and biodeteriorative effects.

Future prospects

(A) Bringing geomicrobiology into the built environment

From this brief survey, only a few main physical and biochemical mechanisms appear to be involved in microbial biodeterioration of human structures, but these are mediated by a diversity of organisms from different taxonomic and metabolic groups, and differing environmental growth requirements¹⁻³. Both prokaryotes and eukaryotes are involved, and with the main exception of SRB-mediated biocorrosion, most significant organisms and processes relating to human-made structures and the built environment are aerobic, with fungi being particularly important agents of biodeterioration. This is unappreciated in many geomicrobial studies of the natural environment where the metabolic diversity of bacteria and archaea has distorted a broader view with the majority of scientific attention being given to these prokaryotes, even to the extent of solely defining them as “microbes”²⁶ to the exclusion of all eukaryotic microorganisms. Clearly, the presence and activities of all groups of microbes and interactions between them should be considered in any geomicrobiological studies, and this should also be the case when considering human-made structures.

In the built environment, most geomicrobial parallels should be drawn from the aerobic natural environment such as rock and mineral surfaces, and the soil “critical zone”¹⁰², which can be defined as “that portion of the terrestrial environment characterized by a significant microbial influence on metal and mineral transformations, organic matter decomposition, and the cycling of other elements”¹⁰³. However, a crucial difference between the natural and built environment is the significance of plant-driven bioweathering^{104,105}, especially the significance of mycorrhizal fungi²⁴. While phototroph-driven microbial communities are significant in bioweathering in the built environment

through algae, cyanobacteria and lichens, this is not always a prerequisite for bioweathering of human-made structures, or indeed in the natural environment^{4,23,58}. Nevertheless, obvious analogies between built and natural environments occur regarding metal and mineral transformations and biodeterioration but often with differences in the composition of microbial communities and dominance of particular species depending on the substrate, location and climate as well as other factors. Modern DNA sequencing approaches have been applied to characterize the indoor microbiome¹⁵, mostly concentrating on bacteria, but these techniques should also be more strenuously applied to the entire geoactive microbial communities and biofilms⁴⁶ colonizing exterior locations for better understanding of the organisms involved and their activities.

(B) Key questions that remain to be answered

It is clear that the built environment provides many different microbially-relevant factors that affect colonization and activity compared to the natural environment. Exterior and interior components of the built environment provide a wealth of surface area, of differing compositions, textures and orientation, and all surfaces can be rapidly inoculated through atmospheric deposition and human contact^{9,13}. Indoor bacterial colonization may be affected by location, e.g. room to room, ceiling versus floor, with differing bacterial communities reflecting different usage patterns rather than effects of the surface material^{10,106}. There is a particular need to assess and understand the importance of substrate and design on microbial colonization and biodeterioration of interior and exterior building components to provide useful information to architects, planners, and builders. Atmospheric pollution, domestic and industrial activities, and animal exudates can further enhance deposition of potential microbial colonizers and nutrients and these processes may need to be dissected in advanced studies. While a variety of methods are available for large-scale investigations, the development of best practices, normalized methods and ideal taxonomic approaches is an ongoing problem to ensure data quality and interpretation¹⁰⁷. To this end, standardized sampling and sequencing protocols may be required to obtain representative data and avoid sample processing biases, while bioinformatics approaches appear to be essential for analysing large metagenomics datasets¹⁰⁷.

Despite many sequencing-based and other surveys of the built environment, there are few detailed studies that combine both functional and taxonomic investigations on mineral weathering³⁶. It is also difficult to separate biotic influences from purely abiotic processes^{4,23,36,71,82}, as is the case in natural environments. While there is little or no information on rates of bioweathering in the built environment, or on its relative significance compared to abiotic weathering, many studies on mineral bioweathering in the soil point to the importance of biotic processes in accelerating or enhancing mineral weathering above abiotic mechanisms^{74,104,105}. Advances in experimental and analytical techniques, such as atomic force, advanced scanning and X-ray microscopy among others, have enabled probing of the fungus-mineral interface at a resolution necessary to allow elucidation of bioweathering mechanisms at the cellular level^{67,104,108}. To extrapolate micron scale observations to the environment, experimental approaches at the macroscale are also required which can be used for modelling^{104,108}, although defining physico-chemical parameters in an organism-substrate interface is extremely challenging^{108,109}. Experimental data combined with mathematical modelling may improve understanding of bioweathering and its significance compared to abiotic processes¹⁰⁸ as well as estimation of weathering rates^{104,110}. Such studies suggest that the contribution of fungal-promoted mineral dissolution to biogeochemical cycling has been significantly underestimated^{74,104}.

Geomicrobiology is, by definition, an interdisciplinary subject area but with its own internal fragmentation, such as the prokaryotic-eukaryotic, and aerobe-anaerobe arenas, that can limit overall understanding of ecosystem functioning. In the context of the built environment, there are clear demarcations in research between bioweathering and biodeterioration studies of external surfaces and structures in the built environment, and of cultural heritage, and the microbiology of the indoor environment conducted largely in the context of human health. Most of the latter studies comprise lists of organisms and their origins, with a preponderance of bacterial attention. There is some commonality in mechanisms of bioweathering and biodeterioration with those occurring in the natural environment but, as discussed previously, there may key differences in the microbial communities involved which may be governed by the nature of the built environment under examination. Multidisciplinary and integrative studies are therefore needed to further understand bioweathering and biodeterioration, not only in the natural environment^{36,111}, but also those affecting human-made structures. Modern molecular techniques such as

genomic sequencing can provide information on metabolic potential, estimate the significance of non-culturable organisms and relative impacts of different microbial groups, and the processes involved³⁶. New bioinformatics approaches have been developed for diversity analyses and the detection of small differences between microbial communities¹¹². Genes, transcripts and proteins could reveal processes and chemical intermediates that are difficult to detect by conventional geochemical approaches¹¹³. Despite these high-throughput approaches, and given the limitations of community and functional analysis, it is clear further endeavour is required to validate their potential. The lack of attention given to eukaryotes and mixed microbial communities, often as biofilms⁴⁶, also requires redress. Undoubtedly, standard laboratory investigations of culturable geoactive microbial species and consortia remain essential for elucidating cell physiology and the chemical, biochemical and biophysical mechanisms they employ¹¹³.

Finally, the impact of climate change will have clear consequences for the built environment, for example through architectural design and development of low energy use buildings, shifts and migrations of human populations, and climatic effects on microbial distribution and survival. It is believed that predicted changes in climate and atmospheric chemistry, e.g. increasing temperature and atmospheric CO₂, may have a profound impact on the structure and geochemical activities of biological communities, including range shifts¹¹⁴, and therefore on the organisms involved in exterior biodeterioration of the built environment and cultural heritage¹¹⁵. The biodeteriorative influence of biotic communities may therefore increase or decrease. Current modelling data suggests that vulnerable sandstone and limestone heritage structures in areas of the Mediterranean, Middle East, Caribbean and Southern Africa may be particularly affected¹¹⁵.

(C) Practical significance and applications

Geomicrobial processes affecting human-made structures can have profound social and economic consequences. Some of these may be problems for the future such as the biodeterioration of nuclear repositories and waste containment systems over the long-term, and the permanent loss of cultural heritage (Figure 2). In view of the extensive new building programmes that are taking place worldwide to accommodate increasing urbanization and

population growth, it is clear that geomicrobial and biodeteriorative influences should receive close attention in their design¹¹⁰. While it is impossible to prevent microbial colonization, especially of exterior locations, better understanding of the geomicrobiology of the built environment, may provide further means of prevention, control or treatment²³, or even the use of microbial systems for bioprotection. The formation of stable patinas or crusts, biofilms and lichen cover can protect the underlying substrate from further weathering, while a fungal-derived copper-oxalate patina was used for bioprotection on a copper artefact¹¹⁶. Some microbial processes may be used in biorestitution or biocleaning approaches, e.g. by removing sulfatic crusts, or degradation of glues used in frescoes^{4,5}. Calcite-bioprecipitating organisms have been used for conservation of stone monuments and stone and concrete reinforcement⁵.

Regarding the indoor environment, understanding of the role of the indoor microbiome in positively or negatively affecting human health has led to the concept of sustainable "bioinformed" buildings that promote well-being, which will clearly necessitate greater communication between scientists and architects⁹. It may even be possible to incorporate design features that alter the indoor microbiome in specific locations⁹. On a broader scale, the application of integrative functional genomic methods to understand molecular dynamics and ecosystems of urban environments has implications for sustainability and future planning¹⁰⁷, especially with the rise of "megacities"¹¹⁷. It may be possible to create density maps of organisms relevant to the built environment, e.g. fungi, as well as determine the impact of building materials on organism distribution. Besides taxonomic and distribution information, genomic data can be mined for other purposes, such as the molecular basis of adaptation and survival¹⁰⁷.

Conclusions

The microbiology of human-made structures can be usefully interpreted by applying knowledge gained from geomicrobiology where there are many general parallels with the natural environment. However, the built environment does offer some particular constraints and benefits for microbial colonization, and diverse microbial communities of both pro- and eukaryotic organisms may be involved. The societal and economic consequences of microbial attack can be profound and provides a continuing

interdisciplinary challenge for researchers, builders, architects, engineers, archaeologists and historians to address. There is an urgent requirement to understand the significant roles of eukaryotes, especially fungi, interactions within mixed microbial communities, and a clear linkage between molecular-based community analysis and function. In addition to assessing the genetic and metabolic diversity of the built environment, functional and geochemical studies with individual isolates and consortia are necessary to clearly define the complex processes involved.

All correspondence to G.M. Gadd.

G.M.G. planned and wrote the article, supplied the figures, and originated the hypotheses, ideas and conclusions therein.

Acknowledgements

Financial support in the author's laboratory is received from the Natural Environment Research Council (NE/M010910/1 (TeaSe); NE/M011275/1 (COG3)) which is gratefully acknowledged. G. M. Gadd also gratefully acknowledges an award under the 1000 Talents Plan with the Xinjiang Institute of Ecology and Geography, Chinese Academy of Sciences, Urumqi, China and support from the National Natural Science Foundation of China (U1503281).

References

1. Ehrlich, H.L. & Newman, D.K. *Geomicrobiology*, 5th edition. Boca Raton, FL: CRC Press/Taylor and Francis Group (2009).
2. Gadd, G.M. Metals, minerals and microbes: geomicrobiology and bioremediation. *Microbiol.* **156**, 609 – 643 (2010).

3. Sand, W. Microbial mechanisms of deterioration of inorganic substrates: a general mechanistic overview. *Int. Biodeterior. Biodegrad.* **40**, 183-190 (1997).
4. Warsheid, T. & Braams, J. Biodeterioration of stone: overview. *Int. Biodeterior. Biodegrad.* **46**, 343–368 (2000).
5. Ranalli, G., Zanardini, E. & Sorlini, C. Biodeterioration – including cultural heritage. In: *Encyclopedia of Microbiology*, Ed: M. Schaecter, pp. 191-205. Elsevier, Oxford.
6. Scheerer, S., Ortega-Morales, O. & Gaylarde, C. Microbial deterioration of stone monuments: an updated overview. *Adv. Appl. Microbiol.* **66**, 97-139 (2009).
7. Cutler, N. & Viles, H. Eukaryotic microorganisms and stone biodeterioration. *Geomicrobiol. J.* **27**, 630–646 (2010).
8. Kembel, S.W. et al. Architectural design drives the biogeography of indoor bacterial communities. *PLoS ONE* **9**(1): e87093. doi:10.1371/journal.pone.0087093 (2014).
9. Brown, G.Z., Kline, J., Mhuireach, G., Northcutt, D., & Stenson, J. Making microbiology of the built environment relevant to design. *Microbiome* **4**, 6. doi: 10.1186/s40168-016-0152-7 (2016).
10. Adams, R.I., Miletto, M., Taylor, J.W. & Bruns, T.D. The diversity and distribution of fungi on residential surfaces. *PLoS ONE* **8**(11): e78866. doi:10.1371/journal.pone.0078866 (2013).
11. Konya, T. & Scott, J.A. Recent advances in the microbiology of the built environment. *Curr. Sustain. Renew. Energy Rep.* **1**, 35–42 (2014).
12. Adams, R.I., Bateman, A.C., Bik, H.M., & Meadow, J.F. Microbiota of the indoor environment: a meta-analysis. *Microbiome* **3**, 49. doi: 10.1186/s40168-015-0108-3 (2015).
13. Leung, M.H.Y. & Lee, P.K.H. The roles of the outdoors and occupants in contributing to a potential pan-microbiome of the built environment: a review. *Microbiome* **4**, 21. doi: 10.1186/s40168-016-0165-2 (2016).
14. Lax, S. et al. Longitudinal analysis of microbial interaction between humans and the indoor environment. *Science* **345**, 1048-1052 (2014).
15. Hoisington, A.J., Brenner, L.A., Kinney, K.A., Postolache, T.T. & Lowry, C.A. The microbiome of the built environment and mental health. *Microbiome* **3**, 60. doi: 10.1186/s40168-015-0127-0 (2015).

- 539 16. Cutler, N.A., Oliver, A.E., Viles, H.A., Ahmad, S. & Whiteley A.S. The characterisation
540 of eukaryotic microbial communities on sandstone buildings in Belfast, UK, using
541 TRFLP and 454 pyrosequencing. *Int. Biodeterior. Biodegrad.* **82**, 124-133 (2013).
- 542 17. Ettenauer, J.D. et al. Microbes on building materials — evaluation of DNA extraction
543 protocols as common basis for molecular analysis. *Sci. Total Environ.* **439**, 44–53
544 (2012).
- 545 18. Amend, A.S., Seifert, K.A., Samson, R. & Bruns, T.D. Indoor fungal composition is
546 geographically patterned and more diverse in temperate zones than in the tropics.
547 *Proc. Nat. Acad. Sci. USA* **107**, 13748–13753 (2010).
- 548 19. Amend, A.S., Seifert, K.A. & Bruns, T.D. Quantifying microbial communities with 454
549 pyrosequencing: does read abundance count? *Mol. Ecol.* **19**, 5555-5565 (2010).
- 550 20. Franzosa, E.A. et al. Sequencing and beyond: integrating molecular ‘omics’ for
551 microbial community profiling. *Nature Rev. Microbiol.* **13**, 360-372.
- 552 21. Gutarowska, B. et al. Metabolomic and high-throughput sequencing analysis - modern
553 approach for the assessment of biodeterioration of materials from historic buildings.
554 *Front. Microbiol.* **6**, 979. doi: 10.3389/fmicb.2015.00979 (2015).
- 555 22. Kelley, S.T. & Gilbert, J.A. Studying the microbiology of the indoor environment.
556 *Genome Biol.* **14**, 202 (2013).
- 557 23. Gorbushina, A.A. Life on the rocks. *Environ. Microbiol.* **9**, 1613-1631 (2007).
- 558 24. Gadd, G.M. Geomycology: biogeochemical transformations of rocks, minerals,
559 metals and radionuclides by fungi, bioweathering and bioremediation. *Mycol. Res.*
560 **111**, 3–49 (2007).
- 561 25. Gadd, G.M. Bacterial and fungal geomicrobiology: a problem with communities?
562 *Geobiol.* **6**, 278–284 (2008).
- 563 26. Druschel, G.K. & Kappler, A. Geomicrobiology and microbial geochemistry. *Elements*
564 **11**, 389-394 (2015).
- 565 27. Sterflinger, K. Fungi as geologic agents. *Geomicrobiol. J.* **17**, 97-124 (2000).
- 566 28. Sterflinger, K. Fungi: their role in deterioration of cultural heritage. *Fungal Biol. Rev.*
567 **24**, 47-55 (2010).
- 568 29. Gadd, G.M. Fungi and their role in the biosphere. In *Encyclopedia of Ecology*, Ed: S.E.
569 Jorgensen and B. Fath, pp. 1709-1717. Elsevier, Amsterdam (2008).

- 570 30. Gadd, G.M. Geomycology. In: *Encyclopedia of Geobiology*, Part 7. Ed: Reitner, J. and
571 Thiel, V., pp. 416-432. Springer, Heidelberg (2011).
- 572 31. Burford, E. P., Fomina, M. & Gadd, G. M. Fungal involvement in bioweathering and
573 biotransformation of rocks and minerals. *Mineral. Mag.* **67**, 1127-1155 (2003b).
- 574 32. Hawksworth, D. To be or not to be a lichen. *Nature* **433**, 468 (2005).
- 575 33. Viles, H. Ecological perspectives on rock surface weathering: towards a conceptual
576 model. *Geomorphol.* **13**, 21-35 (1995).
- 577 34. Seaward, M.R.D. Lichens, agents of monumental destruction. *Microbiol. Today* **30**,
578 110–112 (2003).
- 579 35. Arino, X., Gomez-Bolea, A. & Saiz-Jimenez, C. Lichens on ancient mortars. *Int.*
580 *Biodeterior. Biodegrad.* **40**, 217–224 (1997).
- 581 36. Uroz, S., Calvaruso, C., Turpault, M-P. & Frey-Klett, P. Mineral weathering by
582 bacteria: ecology, actors and mechanisms. *Trends Microbiol.* **17**, 378-387 (2009).
- 583 37. Gadd, G.M. & Raven, J.A. Geomicrobiology of eukaryotic microorganisms.
584 *Geomicrobiol. J.* **27**, 491–519 (2010).
- 585 38. Hoppert, M., Flies, C., Pohl, W., Gunzl, B. & Schneider, J. Colonization strategies of
586 lithobiontic microorganisms on carbonate rocks. *Environ. Geol.* **46**, 421-428 (2004).
- 587 39. Gorbushina, A.A. & Broughton, W.J. Microbiology of the atmosphere-rock interface:
588 how biological interactions and physical stresses modulate a sophisticated microbial
589 ecosystem. *Ann. Rev. Microbiol.* **63**, 431–450 (2009).
- 590 40. Gorbushina, A.A. Fungal activities in subaerial rock-inhabiting microbial
591 communities. In: *Fungi in Biogeochemical Cycles*, ed. G.M. Gadd, pp. 267-288.
592 Cambridge University Press, Cambridge (2006).
- 593 41. Gorbushina, A.A. et al. On the role of black fungi in colour change and
594 biodeterioration of antique marbles. *Geomicrobiol. J.* **11**, 205-221 (1993).
- 595 42. Grote, G. & Krumbein, W. E. Microbial precipitation of manganese by bacteria and
596 fungi from desert rock and rock varnish. *Geomicrobiol. J.* **10**, 49–57 (1992).
- 597 43. Carter, N.E.A. & Viles, H.A. Bioprotection explored: the story of a little known earth
598 surface process. *Geomorphol.* **67**, 273–281 (2005).
- 599 44. McIlroy de la Rosa, J.P., Warke, P.A. & Smith, B.J. The effects of lichen cover upon
600 the rate of solutional weathering of limestone. *Geomorphol.* **220**, 81-92 (2014).

45. Jurado, V. et al. Recolonization of mortars by endolithic organisms on the walls of San Roque church in Campeche (Mexico): a case of tertiary bioreceptivity. *Constr. Build. Materials* **53**, 348-359 (2014).
46. Flemming, H-C. et al. Biofilms: an emergent form of bacterial life. *Nature Rev. Microbiol.* **14**, 563-575 (2016).
47. Walker, J.J. & Pace, N.R. Endolithic microbial ecosystems. *Ann. Rev. Microbiol.* **61**, 331–347 (2007).
48. Kumar, R. & Kumar, A. V. *Biodeterioration of stone in tropical environments: an overview*. Madison, USA: the J. Paul Getty Trust (1999).
49. Gleeson, D.B., Clipson, N.J.W., Melville, K., Gadd, G.M. & McDermott, F.P. Mineralogical control of fungal community structure in a weathered pegmatitic granite. *Microb. Ecol.* **50**, 360-368 (2005).
50. Gleeson, D.B. et al. Mineralogical influences on bacterial community structure on a weathered pegmatitic granite. *Microb. Ecol.* **51**, 526-534 (2006).
51. Gleeson, D.B., Melville, K., McDermott, F.P., Clipson, N.J.W. & Gadd, G.M. Molecular characterization of fungal communities in sandstone. *Geomicrobiol. J.* **27**, 559-571 (2010).
52. Coutinho, M.L., Miller, A.Z. & Macedo, M.F. Biological colonization and biodeterioration of architectural ceramic materials: an overview. *J. Cult. Heritage* **16**, 759-777 (2015).
53. Cwalina, B. Biodeterioration of concrete, brick and other mineral-based building materials. In *Understanding Biocorrosion*. Ed: Liengen, T., Feron, D., Basseguy, R. & Beech, I.B., pp. 281-312. Elsevier, Amsterdam (2014).
54. Zhdanova, N.N., Zakharchenko, V.A., Vember, V.V. & Nakonechnaya, L.T. Fungi from Chernobyl: mycobiota of the inner regions of the containment structures of the damaged nuclear reactor. *Mycol. Res.* **104**, 1421–1426 (2000).
55. Gaylarde, C. & Gaylarde, P.M. A comparative study of the major microbial biomass of biofilms on exteriors of buildings in Europe and Latin America. *Int. Biodeterior. Biodegrad.* **55**, 131-139 (2005).
56. De la Torre, M.A., Gomez-Alarcon, G., Vizcaino, C. & Garcia, M.T. Biochemical mechanisms of stone alteration carried out by filamentous fungi living on monuments. *Biogeochem.* **19**, 129–147 (1993).

57. Koestler, R.J., Warscheid, T. & Nieto, F. Biodeterioration risk factors and their management. In: *Saving our Cultural Heritage: the Conservation of Historic Stone Structures*, pp. 25-36. Wiley, New York (1997).
58. Roeselers, G., van Loosdrecht, M.C.M. & Muyzer, G. Heterotrophic pioneers facilitate phototrophic biofilm development. *Microb. Ecol.* **54**, 578–585 (2007).
59. Mitchell, R. & Gu, J.-D. Changes in the biofilm microflora of limestone caused by atmospheric pollutants. *Int. Biodeterior. Biodegrad.* **46**, 299-303 (2000).
60. Hutchens, E. Microbial selectivity on mineral surfaces: possible implications for weathering processes. *Fungal Biol. Rev.* **23**, 115-121 (2009).
61. Turick, C.E. & Berry, C.J. Review of concrete biodeterioration in relation to nuclear waste. *J. Environ. Radioact.* **151**, 12-21 (2016).
62. Jongmans, A.G. et al. Rock-eating fungi. *Nature* **389**, 682–683 (1997).
63. Lisci, M., Monte, M. & Pacini, E. Lichens and higher plants on stone: a review. *Int. Biodeterior. Biodegrad.* **51**, 1 – 17 (2003).
64. Smits, M. Mineral tunnelling by fungi. In *Fungi in Biogeochemical Cycles* (Gadd, G.M., ed.), pp. 311–327, Cambridge: Cambridge University Press (2006).
65. Lian, B., Chen, Y., Zhu, L. & Yang, R., Effect of microbial weathering on carbonate rocks. *Earth Sci. Front.* **15**, 90–99 (2008a).
66. Cockell, C.S. & Herrera, A. Why are some microorganisms boring? *Trends Microbiol.* **16**, 101-106 (2008).
67. McMaster, T.J. Atomic force microscopy of the fungi-mineral interface: applications in mineral dissolution, weathering and biogeochemistry. *Curr. Opinion Biotechnol.* **23**, 562-569 (2012).
68. Chen, J., Blume, H-P. & Beyer, L. Weathering of rocks induced by lichen colonization - a review. *Catena* **39**, 121–146 (2000).
69. De los Rios, A., Galvan, V. & Ascaso, C. *In situ* microscopical diagnosis of biodeterioration processes at the convent of Santa Cruz la Real, Segovia, Spain. *Int. Biodeterior. Biodegrad.* **51**, 113–120 (2004).
70. Gadd, G. M. et al. Oxalate production by fungi: significance in geomycology, biodeterioration and bioremediation. *Fungal Biol. Rev.* **28**, 36–55 (2014).

71. Barker, W.W. & Banfield, J.F. Biologically versus inorganically mediated weathering reactions: relationships between minerals and extracellular microbial polymers in lithobiotic communities. *Chem. Geol.* **132**, 55-69 (1996).
72. Wright, J. S. Geomorphology and stone conservation: sandstone decay in Stoke-on-Trent. *Struct. Surv.* **20**, 50–61 (2002).
73. Barker, W.W. & Banfield, J.F. Zones of chemical and physical interaction at interfaces between microbial communities and minerals: a model. *Geomicrobiol. J.* **15**, 223-244 (1998).
74. Li, Z., Liu, L., Chen, J. & Chen, H.H. Cellular dissolution at hypha- and spore-mineral interfaces revealing unrecognized mechanisms and scales of fungal weathering. *Geology*, Data Repository Item 2016094, doi: 10.1130/G37561.1 (2016).
75. Kim, B.H. & Gadd, G.M. *Bacterial Physiology and Metabolism*. Cambridge: Cambridge University Press (2008).
76. Fomina, M. et al. Fungal deterioration of barrier concrete used in nuclear waste disposal. *Geomicrobiol. J.* **24**, 643-653 (2007).
77. Nica, D., Davis, J.L., Kirby, L., Zuo, G. & Roberts, D.J. Isolation and characterization of microorganisms involved in the biodeterioration of concrete in sewers. *Int. Biodeter. Biodegrad.* **46**, 61-68 (2000).
78. Gadd, G.M. Fungal production of citric and oxalic acid: importance in metal speciation, physiology and biogeochemical processes. *Adv. Microb. Physiol.* **41**, 47–92 (1999).
79. Fomina, M., Burford, E.P., Hillier, S., Kierans, M. & Gadd, G.M. Rock-building fungi. *Geomicrobiol. J.* **27**, 624–629 (2010).
80. Brehm, U., Gorbushina, A. & Mottershead, D. The role of microorganisms and biofilms in the breakdown and dissolution of quartz and glass. *Palaeogeol. Palaeoclim. Palaeoecol.* **219**, 117-129 (2005).
81. Dedesko, S. & Siegel, J.A. Moisture parameters and fungal communities associated with gypsum drywall in buildings. *Microbiome* **3**, 71. doi: 10.1186/s40168-015-0137-y (2015).
82. Beech, I.B. & Sunner, J. Biocorrosion: towards understanding interactions between biofilms and metals. *Curr. Opinion Biotechnol.* **15**, 181–186 (2004).

- 694 83. Gu, J.-D. Corrosion, microbial. In *Encyclopedia of Microbiology*, 3rd Edition, pp. 259-
695 269. Edited by M. Schaechter. Amsterdam: Elsevier (2009).
- 696 84. Rhee, Y.J., Hillier, S., Pendlowski, H. & Gadd, G.M. Pyromorphite formation in a
697 fungal biofilm community growing on lead metal. *Environ. Microbiol.* **16**, 1441–1451
698 (2014).
- 699 85. Nealson, K.H. & Conrad, P.G. Life: past, present and future. *Phil. Trans. R. Soc. Lond.*
700 **354**, 1923-1939 (1999).
- 701 86. Wimpenny, J.W.T. & Kinniment, S. Biochemical reactions and the establishment of
702 gradients within biofilms. In: *Microbial Biofilms, Vol. 1*. Ed: Lappin-Scott, H.M.,
703 Costerton, J.W., pp. 99-117. Cambridge University Press, Cambridge (1995).
- 704 87. Aramendia, J. et al. Bioimpact on weathering steel surfaces: oxalates formation and
705 the elucidation of their origin. *Int. Biodeterior. Biodegrad.* **104**, 59-66 (2015).
- 706 88. Favero-Longo, S.E., Castelli, D., Fubini, B. & Piervittori, R. Lichens on asbestos–
707 cement roofs: bioweathering and biocovering effects. *J. Hazard. Mat.* **162**, 1300–
708 1308 (2009).
- 709 89. Favero-Longo, S.E. et al. Chrysotile asbestos is progressively converted into a non-
710 fibrous amorphous material by the chelating action of lichen metabolites. *J. Environ.*
711 *Monitor.* **7**, 764–766 (2005).
- 712 90. De la Fuente, D., Simancas, J. & Morcillo, M. Morphological study of 16-year patinas
713 formed on copper in a wide range of atmospheric exposures. *Corr. Sci.* **50**, 268–285
714 (2008).
- 715 91. Del Monte, M., Sabbioni, C. & Zappia, G. The origin of calcium oxalates on historical
716 buildings, monuments and natural outcrops. *Sci.Total Environ.* **67**, 17-39 (1987).
- 717 92. Radeka, M., Ranogajec, J., Kiurski, J., Markov, S. & Marinkovic-Neducin, R. Influence
718 of lichen biocorrosion on the quality of ceramic roofing tiles. *J. Eur. Ceram. Soc.* **27**,
719 1763–1766 (2007).
- 720 93. Piñar, G. et al. Microscopic, chemical, and molecular-biological investigation of the
721 decayed medieval stained window glasses of two Catalanian churches. *Int.*
722 *Biodeterior. Biodegrad.* **84**, 388-400 (2013).
- 723 94. Gaylarde, C., Ribas Silva, M. & Warscheid, T. Microbial impact on building materials:
724 an overview. *Materials Struct.* **36**, 342-352 (2003).

95. Urzi, C., Criseo, G., Krumbein, W.E., Wollenzien, U. & Gorbushina, A.A. Are colour changes of rocks caused by climate, pollution, biological growth, or by interaction of the three? In: *Conservation of Stone and Other Materials*, Ed: Thiel, M.J., pp. 279-286. E. & F.N. Spon.: London (1993).
96. Saiz-Jiminez, C. Biodeterioration vs biodegradation: the role of microorganisms in the removal of pollutants deposited on historic buildings. *Int. Biodeterior. Biodegrad.* **40**, 225-232 (1997).
97. Gaylarde, C. et al. Interactions between fungi of standard paint test method BS3900. *Int. Biodeterior. Biodegrad.* **104**, 411-418 (2015).
98. Miletto, M. & Lindow, S.E. Relative and contextual contribution of different sources to the composition and abundance of indoor air bacteria in residences. *Microbiome* **3**, 61. doi: 10.1186/s40168-015-0128-z (2015).
99. Stetzenbach, L.D., Amman, H., Johanning, E., King, G. & Shaughnessy, R.J. *Microorganisms, mold and indoor air quality*. American Society for Microbiology, Washington DC (2004).
100. Sterflinger, K. & Pinzari, F. The revenge of time: fungal deterioration of cultural heritage with particular reference to books, paper and parchment. *Environ. Microbiol.* **14**, 559–566 (2012).
101. Pinzari, F., Zotti, M., De Mico, A. & Calvini, P. Biodegradation of inorganic components in paper documents: formation of calcium oxalate crystals as a consequence of *Aspergillus terreus* Thom growth. *Int. Biodeterior. Biodegrad.* **64**, 499–505 (2010).
102. Brantley, S.L., Goldhaber, M.B. and Ragnarsdottir, K.V. Crossing disciplines and scales to understand the critical zone. *Elements* **3**, 307-314 (2007).
103. Gadd, G.M. Microbial roles in mineral transformations and metal cycling in the Earth's critical zone. In: *Molecular Environmental Soil Science*. Ed. Xu, J., Sparks, D.L., pp. 115-165. Springer, Dordrecht (2013).
104. Bonneville, S. et al. Tree-mycorrhiza symbiosis accelerate mineral weathering: evidences from nanometer-scale elemental fluxes at the hypha-mineral interface. *Geochim. Cosmochim. Acta* **75**, 6988-7005 (2011).

105. Smits, M.M., Bonneville, S., Benning, L.G., Banwart, S.A. & Leake, J.R. Plant-driven weathering of apatite – the role of an ectomycorrhizal fungus. *Geobiol.* **10**, 445–456 (2012).
106. Chase, J. et al. Geography and location are the primary drivers of office microbiome composition. *mSystems* **1**, e00022-16. doi:10.1128/mSystems.00022-16 (2016).
107. The MetaSUB International Consortium. The Metagenomics and Metadesign of the Subways and Urban Biomes (MetaSUB) International Consortium inaugural meeting report. *Microbiome* **4**, 24 doi: 10.1186/s40168-016-0168-z (2016).
108. Smits, M.M. et al. The fungal-mineral interface: challenges and considerations of micro-analytical developments. *Fungal Biol. Rev.* **23**, 122-131 (2009).
109. Rosling, A. et al. Approaches to modelling mineral weathering by fungi. *Fungal Biol. Rev.* **23**, 1–7 (2009).
110. Sverdrup, H. Chemical weathering of soil minerals and the role of biological processes. *Fungal Biol. Rev.* **23**, 94–100 (2009).
111. Moses, C., Robinson, D. & Barlow, J. Methods for measuring rock surface weathering and erosion: a critical review. *Earth-Sci. Rev.* **135**, 141-161 (2014).
112. Fouquier, J. et al. Ghost-tree: creating hybrid-gene phylogenetic trees for diversity analyses. *Microbiome* **4**, 11 doi: 10.1186/s40168-016-0153-6 (2016).
113. Dick, G.J. & Lam, P. Omic approaches to microbial geochemistry. *Elements* **11**, 403-408 (2015).
114. Brantley, S.L. et al. Twelve testable hypotheses on the geobiology of weathering. *Geobiol.* **9**, 140-165 (2011).
115. Viles, H.A. & Cutler, N.A. Global environmental change and the biology of heritage structures. *Global Change Biol.* **18**, 2406–2418 (2012).
116. Joseph, E. et al. Protection of metal artifacts with the formation of metal–oxalates complexes by *Beauveria bassiana*. *Front. Microbiol.* **2**, 270. doi: 10.3389/fmicb.2011.00270 (2012).
117. Lyons, W.B. & Harmon, R.S. Why urban geochemistry? *Elements* **8**, 417-422 (2012).
118. Sabbioni, C., Ghedini, N. & Bonazza, A. Organic anions in damage layers on monuments and buildings. *Atmos. Environ.* **37**, 1261–1269 (2003).

119. Garcia-Valles, M., Vendrell-Saz, M., Krumbein, W.E. & Urzi, C. Coloured mineral coatings on monument surfaces as a result of biomineralization: the case of the Tarragona cathedral (Catalonia). *Appl. Geochem.* **12**, 255-266 (1997).
120. Monte, M. Oxalate film formation on marble specimens caused by fungus. *J. Cultural Heritage* **4**, 255–258 (2003).
121. Rosado, T., Gil, M., Mirão, J., Candeias, A. & Caldeir, A.T. Oxalate biofilm formation in mural paintings due to microorganisms - a comprehensive study. *Int. Biodeterior. Biodegrad.* **85**, 1-7 (2013).
122. Pinzari, F., Tate, J., Bicchieri, M., Rhee, Y.J., & Gadd, G.M. Biodegradation of ivory (natural apatite): possible involvement of fungal activity in biodeterioration of the Lewis Chessmen. *Environ. Microbiol.* **15**, 1050–1062 (2013).

798 **Glossary**

799

800 chemolithotroph – an organism that obtains its energy from the oxidation of inorganic
801 compounds.

802

803 chemoorganotroph – an organism that obtains its energy from the oxidation of organic
804 compounds.

805

806 phototroph – an organism that uses light as its principal source of energy for the
807 manufacture of organic compounds.

808

Box 1. The impact of biodeterioration on cultural heritage

In a societal context, a significant proportion of world cultural heritage is constructed of stone and biodeterioration can represent a permanent loss^{5,6}. The most common stone types affected are marble, limestone, sandstone and granite, while materials used to stabilize building blocks (mortar) and to coat surfaces prior to painting (plaster or stucco) can also be extremely susceptible to degradation⁶. Stone cultural heritage includes buildings, paved surfaces, stone monuments, e.g. statues and gravestones), archaeological artefacts and rock art⁷. The human societal impact of geomicrobial processes on these structures includes biodeterioration, discolouration and staining, structural damage and decay, biocorrosion, altered metal mobility, and permanent disappearance. Aesthetic, cultural and economic consequences can therefore be profound (Figure 2).

Organic acids are very important bioweathering agents of cultural heritage monuments, statues, rock paintings, friezes and frescoes^{4,7,63,70,78,91,118}. Calcium oxalates (whewellite and weddellite) occur widely in patinas on the surfaces of marble and limestone buildings and monuments, as well as on sandstone, granite, plasters, cave and wall paintings and sculptures^{27,119-121}.

Many chemoorganotrophic bacteria, archaea and fungi can colonize and deteriorate artwork including murals^{5,28}. For cultural heritage, fungal growth in wall murals and frescoes can cause structural damage, and calcium and other oxalates may be produced from the calcite or metal- and mineral-containing pigments in the paint used. This can cause efflorescence, cracking, peeling and spalling of outer layers, as well as colour changes and stains^{118,121}. Fungi can also degrade wood, textiles, paper, parchments, leather, glue, bone, ivory and other materials used in historical objects^{28,122}.

834

835 **Figure 1.** Some of the main influences and effects of microorganisms on components of the
836 built environment and human-made structures. There can be many dynamic interactions
837 between a multiplicity of physical and biochemical mechanisms in biodeterioration of rock
838 and mineral-based substrates. Biophysical mechanisms include penetration and boring;
839 secondary mineral formation; EPS or biomass swelling or contraction; removal of lichen
840 thalli and adhering substratum by animals and the weather; cell turgor pressure; physical
841 and chemical effects caused by microbial alteration of habitat geochemistry, e.g, changes in
842 pH, redox potential, porosity, water retention, and aerobic/anaerobic transitions.
843 Biochemical mechanisms include metabolite excretion, e.g. H^+ , CO_2 ; organic acids, e.g. citric,
844 oxalic; inorganic acids, e.g. sulfuric, nitric and carbonic; production of metal-complexing EPS,
845 solvents and emulsifying agents; Fe(III)-coordinating siderophores; redox transformations by
846 oxidation or reduction; bioaccumulation of solubilized metal and anionic species;
847 biomineralization and formation of, e.g. carbonates, phosphates, sulfides, oxides and
848 oxalates; alteration of habitat geochemistry by metabolism affecting metal and anionic
849 speciation and mobility. Biodegradation of organic substances can be achieved by
850 extracellular enzymic attack affecting many organic substrates including wood, plastics,
851 paint, leather, paper, glues, resins, waxes, and protective coatings. Biocorrosion of metals
852 and alloys can include sulfate reduction and metal sulfide precipitation; acid effects; redox
853 transformations; formation of localized corrosion cells; metal complexation by exopolymers,
854 organic acids and other metabolites; and secondary mineral formation. Scale bars on the
855 micrographs are 50 μm .

856

Figure 2. Examples of biofouling, discolouration, staining and biodeterioration of cultural heritage predominantly caused by algae, fungi and lichens. Greening can be the result of colonization by phototrophic microorganisms: cyanobacteria, algae and lichens. Blackening is mainly due to dark-pigmented fungi and also patina development due to various mineralogical transformations. Various colours can reflect photosynthetic or other pigments, as well as metal-mineral transformations. (a,e) historical statues (Stadio Olimpico, Rome, Italy) (b) gravestone (St Kenelm's Church, Minster Lovell, Oxfordshire) (c) gravestone (Dunbarney Burial Ground, Perth and Kinross, Scotland) (d) religious wall art and fresco (Flavigny, Burgundy, France) (f) St. Stephen's Cathedral, Vienna, Austria (g,k) monastery (Mosteiro dos Jeronimos, Belem, Portugal) (h) historic stonework (near Charlbury, Oxfordshire, England, UK) (i) ornamental fountain (Fontenay Abbey, Montbard, Burgundy, France) (j) religious wall fresco (Flavigny, Burgundy, France). Images taken by G.M. Gadd.