University of Dundee

Applications of nanozymes in the environment

Meng, Yutong; Li, Wenfeng; Pan, Xiangliang; Gadd, Geoffrey Michael

Published in:
Environmental Science: Nano

DOI:
[10.1039/c9en01089k](https://doi.org/10.1039/c9en01089k)

Publication date:
2020

Document Version
Peer reviewed version

[Link to publication in Discovery Research Portal](#)

Citation for published version (APA):
Meng, Y., Li, W., Pan, X., & Gadd, G. M. (2020). Applications of nanozymes in the environment. *Environmental Science: Nano*, 7(5), 1305-1318. <https://doi.org/10.1039/c9en01089k>

General rights

Copyright and moral rights for the publications made accessible in Discovery Research Portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from Discovery Research Portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain.
- You may freely distribute the URL identifying the publication in the public portal.

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Applications of nanozymes in the environment

Abstract: Nanozymes are inorganic nanoparticles that mimic the enzyme-like properties in redox reactions, possessing both unique properties of nanomaterials and a catalytic function. Because of high catalytic activity, stability and multifunctionality, nanozyme are of increasingly wide interest in the fields of environmental science and technology. In this article, we review the most recent advances of nanozyme research for environmental pollutant detection and treatment. Nanozymes can be used to detect ions, molecules and organic compounds both qualitatively and quantitatively. They have also been applied for destruction multi-drug resistant bacteria and the degradation of various organic pollutants. Despite the apparent potential of nanozymes in environmental science and technology, current research and application is still limited, and so future challenges and research prospects have been highlighted.

Keywords: nanozyme; heavy metals; organic pollutants; antibacterial substances; organic pollutant degradation

1. Introduction

1.1 Definition of nanozyme

Most life processes in nature involve “enzymes”. Natural enzymes are a class of biomolecules that process catalytic functions.¹ They are mainly proteins, and their catalytic activity on the substrate can be very efficient and high specific.² However, since most natural enzymes are inhibited and denatured by non-physiological or adverse conditions, such as heat, acids, and alkalis, they are prone to degeneration and can lose their function.³⁻⁵ With the rapid development of nanoscience,

nanotechnology and the development of nanomaterials have entered various branches of the life sciences.^{6, 7}

In early research, the superoxide dismutase (SOD) mimicking activities of fullerene derivatives was discovered.^{8, 9} Subsequently it was found that the inorganic nanomaterial Fe₃O₄ processed a biological activity similar to that of the natural enzyme, horseradish peroxidase (HRP).^{10, 11} Since then, the “nanozyme” concept has developed and the subyear of increasing numbers of research publications.¹²⁻²⁴

Nanozymes are inorganic nanoparticles that mimic enzyme-like properties in redox reactions, therefore processing both unique properties of nanomaterials and a catalytic function.^{14, 23, 25-27} Because of high catalytic activity, stability and multifunctionality, nanozymes have found increasingly wide potential applications in fields, such as medicine, chemical engineering, agriculture and the environment.^{21, 22, 28-32} In fact, nanomaterials were originally considered as being a chemically inert material with no intrinsic biological effects, a nanozyme was originally defined as an enzyme or enzymic catalytic group associated with the nanomaterial surface and termed a nanomaterial hybridizing enzyme.^{33, 34} For example, azacrown was modified onto gold nanoparticles (AuNP) by chelation with Zn²⁺ to imbue catalytic activity in shearing phosphodiester bonds mimicking the function of RNase³⁵. Thus the catalytic activity arises from surface-modified components and not from the nature of the nanomaterials themselves. However, with the further development and application of nanomaterials, several nanomaterials have been found to process inherent enzymic catalytic properties, and therefore, the definition of nanozyme has become broader to include all nanomaterials that possess intrinsic enzyme-like activities.³⁶

1.2 Classification and catalytic mechanisms of nanozyme

Nanozymes vary in structure and composition, and include metal oxides,³⁷⁻⁵² metals,^{17, 53-71} and carbon-based nanomaterials.⁷²⁻⁷⁸ However, most of the catalytic reactions mediated by nanozymes employ the following four kinds of enzymic reactions: oxidase (OXD), peroxidase (POD), catalase (CAT) and superoxide dismutase (SOD) (Table 1).

Table 1 Current nanomaterials as enzyme mimics and their typical applications and representative references (GO: graphene oxide, PANI: polyaniline, rGO: reduced graphene oxide, C-dots: carbon dots, NPs: nanoparticles, CAT-NP: catalytic nanoparticles, Dex-NZM: dextran-coated iron oxide nanoparticles termed nanozymes, GQD: Graphene quantum dot, MNP@CTS: ferromagnetic chitosan nanozyme, OXD: oxidase, POD: peroxidase, CAT: catalase, SOD: superoxide dismutase, HRP: Horseradish Peroxidase)

Application	Nanomaterial	Enzyme type	Reference
Detection of ions	MoS ₂	POD	104
	Fe ₃ O ₄	POD	105
	Au	POD	106
	CoO _x H-GO	POD	108
Detection of organic pollutants	PdAu	POD	112
	PANI/rGO	CAT	115
	MnO ₂	OXD	117
Antimicrobial and antifouling treatments	MoS ₂	POD	133
	C-dots	OXD	134
	C ₃ N ₄ @AuNPs	POD	123
	CAT-NP with Fe ₃ O ₄	POD	135
	CuO NPs	POD	138
	CuO nanorods	POD	139
	Nanoceria	SOD and CAT	140
	Dex-NZM	POD	136
	CeO _{2-x} nanorods	HRP	141
	GQD	POD	72,143
Treatment of organic pollutants	MNP@CTS	POD	149
	MnP	POD	150
	LiP	POD	153
	ZnO/CuO	POD	157
	Au/TiO ₂	POD	158
	Nano-eco-enzyme	POD	159,160

Natural OXDs are enzymes that catalyze an oxidation-reduction reaction, especially those involving dioxygen (O₂) as the electron acceptor.⁷⁹ Nanozymes based on gold⁸⁰⁻⁸⁶ and copper^{87, 88} are typical

representatives of OXD mimic enzymes.³⁴ The proposed mechanism of molecular activation for AuNP catalysis is shown in Figure 1. The hydrated glucose anion is first adsorbed onto the surface of the AuNP, and the interaction with gold surface atoms forms an electron-rich gold species which effectively activates molecular oxygen by nucleophilic attack and produces a dioxo-gold intermediate. The Au^+-O_2^- or $\text{Au}^{2+}-\text{O}_2^{2-}$ couples of the dioxo-gold intermediate serve as a bridge to transfer electrons from glucose to dioxygen. Finally, gluconic acid and H_2O_2 are produced.^{33, 34}

Fig. 1 Gold nanoparticles exhibit a catalytic mechanism that mimics glucose oxidase (reproduced with permission from ref. 86, Copyright 2006 Wiley-VCH).

PODs can commonly attack peroxides.⁸⁹ Fe_3O_4 magnetic materials possess intrinsic POD properties¹⁰ and these have been applied for the detection of both H_2O_2 and glucose.⁹⁰ Other iron oxide-based POD mimics have also been studied, including Fe_3O_4 ,^{91, 92} Fe_2O_3 ,^{93, 94} and doped ferrites.⁹⁵ Since POD-like iron oxide has a Fenton and/or Haber-Weiss reaction mechanism (possibly involving $\cdot\text{OH}$ / $\text{HO}_2\cdot$), nanozymes can be used for organic pollutant degradation by combining free radical production with magnetic properties of iron oxide.³⁴

CATs catalyze the decomposition of hydrogen peroxide to water and oxygen.⁹⁶ CeO_2 NPs can serve as CAT mimic enzymes.⁹⁷ A series of catalytic effects is achieved by a redox reaction that forms catalytically effective Ce^{4+} . Ce^{4+} is reduced by H_2O_2 to form Ce^{3+} and produces protons and O_2 . After that, another H_2O_2 molecule can combine with the oxygen vacancy in reaction (5), oxidizing Ce^{3+} to

76 Ce^{4+} , and releasing H_2O (Fig. 2).^{33, 98}

77

78 **Fig. 2** Mechanism of CeO_2 nanoparticles acting as catalase mimic enzymes (reproduced with permission from ref. 98, Copyright 2011

79 Royal Society of Chemistry).

80 SOD is an enzyme that alternately catalyzes the dismutation (or partitioning) of the superoxide ($\text{O}_2^{\cdot-}$)

81 radical into either molecular oxygen (O_2) or hydrogen peroxide (H_2O_2).⁹⁹ Taking Cu SOD as an

82 example, as a reducing agent, $\text{O}_2^{\cdot-}$ is finally turned into O_2 : $\text{Cu}^{2+}\text{-SOD} + \text{O}_2^{\cdot-} \rightarrow \text{Cu}^+\text{-SOD} + \text{O}_2$.¹⁰⁰

83 These kinds of redox reactions can produce (or eliminate) free radicals and regulate levels of reactive

84 oxygen species (ROS). Because ROS can attack nucleic acids, proteins, polysaccharides, lipids and

85 other biological molecules, ROS releasing nanozymes can have excellent antimicrobial properties.¹⁰¹ In

86 addition, POD-mimic nanozymes can produce hydroxyl radicals with oxidative properties. Due to these

87 characteristics, nanozymes have been widely applied to environmental problems. Nanozymes can

88 detect the presence of certain pollutants, and also be used for effective treatment.

Fig. 3 Natural enzymic properties, advantages and applications of nanozymes (R: substrate, OXD: oxidase, POD: peroxidase, CAT:

catalase, SOD: superoxide dismutase) (reproduced with permission from ref. 33, Copyright 2019, American Chemical Society).

Table 2 Nanomaterials for detection as enzyme mimics and their targets and agents (PANI: polyaniline, rGO: reduced graphene oxide, OXD: oxidase, POD: peroxidase, CAT: catalase) (adapted from refs.104-108,112,115,117)

Nanomaterial	Enzyme type	Agent	Target
MoS ₂	POD	2, 3-diaminophenazine	Fe ²⁺
Fe ₃ O ₄	POD	4-chloro-1-naphthol	Ag ⁺
Au	POD	4-nitrophenol	Hg ²⁺
CoO _x H-GO	POD	Amplex Red	CN ⁻
PdAu	POD	O-phenylenediamine	Malathion
PANI/rGO	CAT	Electrical signal	Kanamycin
MnO ₂	OXD	Oligonucleotides	Ochratoxin A

2. Nanozymes for the detection of environmental pollutants

Nanozymes can be used in place of natural enzymes for environmental monitoring. By employing the catalytic activity of POD nanozymes, the content of hydrogen peroxide in rainwater, acid rain, and heavy metals, including mercury, can be detected in environmental samples. Such nanozyme detection methods are also suitable for operation under various environmental conditions and are relatively simple and inexpensive, and can be easily applied to screening of, e.g. pesticides, organophosphorus compounds, and other substances.

Whether the pollutants are ions, metals or organic compounds, nanozymes can only detect them indirectly. The basic principle of detection is that the target activates a reaction between the nanozyme and the agent, or the presence of the nanozyme causes the target to undergo a change in chemical properties and reacts with the agent to be detected (Fig. 4). An agent is usually a colorimetric sensor although there is some use of sensors such as electric current monitors (Table 2).

2.1 Detection of Ions

In the field of environmental pollution, the term heavy metals, mainly refers to such potentially biotoxic elements as mercury, cadmium, lead, chromium and arsenic. Heavy metals cannot be degraded, only transformed into different chemical species by abiotic or biotic mechanism, and they can be biologically amplified through food webs, causing harm to ecosystems and organisms, including humans.^{102, 103}

A novel layered molybdenum disulfide (MoS_2) nanosheet POD mimetic-based fluorescent catalytic biosensor was developed for the sensitive and selective detection of Fe^{2+} over the range of 0.005-0.20 μM .¹⁰⁴ The catalyst MoS_2 , was synthesized from $\text{Na}_2\text{MoO}_4 \cdot 2\text{H}_2\text{O}$, and exhibits POD activity. O-phenylenediamine acts as the substrate and was converted to 2, 3-diaminophenazine by MoS_2 in the presence of Fe^{2+} , becoming an indicator of fluorescence detection. Since the fluorescence intensity was proportional to the Fe^{2+} concentration, Fe^{2+} was successfully detected with high selectivity and sensitivity.

Fig. 4 The basic principle of nanozyme detection of ions/organic compounds (PANI: polyaniline, rGO: reduced graphene oxide) (adapted from refs.104-106,108,112,115,117)

Based on the POD-like properties of histidine-modified Fe_3O_4 (his- Fe_3O_4) nanozyme, a simple, low-cost means to detect Ag^+ was developed with ultralow detection limit of 18 fg/mL.¹⁰⁵ An electron transfer sensor was conjugated to the highly active nanozyme his- Fe_3O_4 in the presence of Ag^+ via a specific reaction. 4-chloro-1-naphthol was used as the substrate, nanozyme his- Fe_3O_4 was used as the catalyst, and H_2O_2 was used as an oxidant. When Ag^+ was present, the POD enzyme activity of his- Fe_3O_4 was activated and this changed the substrate to generate insulating precipitation of benzo-4-chlorohexadienone. The insulating products attenuate the photocurrent signal which reflected the presence of Ag^+ . His- Fe_3O_4 nanozymes could make photoelectrochemical immunoassays chemical easier and less expensive.

Mercury in the environment exists in many chemical forms, with divalent mercury being one of the most stable. Because of the toxicity and bioaccumulation potential of mercury, detection in the environment is very important. One approach harnessed the strong affinity between AuNP and Hg^{2+} , meaning that mercury can attach to the surface of gold nanozymes to form a gold amalgam. As a POD nanozyme, AuNP activity was further enhanced by precipitation of Hg^{2+} , and NaBH_4 supplied as a

reducing agent, reduce the substrate 4-nitrophenol more quickly. 4-nitrophenol reduction produces a colour change with ultra-high sensitivity to Hg^{2+} and detection limits down to 1.45 nM. This AuNP nanozyme was stable and recyclable.^{106, 107}

A cobalt oxide/oxide-modified graphene oxide ($\text{CoO}_x\text{H-GO}$) nanozyme having POD-like catalytic activity has been used as an effective detecting agent for CN^- (selectivity>100-fold).¹⁰⁸ The principle relied on the significant inhibitory effect of CN^- on the catalytic activity of the $\text{CoO}_x\text{H-GO}$ nanozyme. When Amplex Red was used as a substrate and colorimetric reagent, with the $\text{CoO}_x\text{H-GO}$ nanozyme as catalyst and H_2O_2 as oxidant, the increase in CN^- concentration was clearly reflected by a decrease in red colour. This method can also be applied to complex wastewaters (e.g. sea water) at low cost.

2.2 Detection of organic pollutants

There are several kinds of organic pollutants in the environment, and many are difficult to detect. Nanozymes can be used to detect pesticides, antibiotics and other toxic organic compounds.¹⁰⁹⁻¹¹¹

Pesticide pollution refers to pollution caused by pesticides, and their toxic metabolites, degradation products and impurities remaining in organisms, agricultural by-products and the environment after pesticide use has exceeded the maximum residue limits. The toxicity of residual pesticides to living organisms is called the pesticide residue, and this can contaminate the soil, atmosphere and groundwater. In order to detect pesticide residues, various nanozymes have been examined. For example, O-phenylenediamine was used as the substance to be oxidized, and palladium-gold (PdAu) bimetallic nanozyme as the catalyst. Because the POD activity of nanozyme was selectively quenched with increasing concentrations of malathion, is PdAu nanozyme could be used for detection of is low-toxic insecticide. This assay was highly sensitive (60 ng/ml) and of low

cost.¹¹²⁻¹¹⁴

Kanamycin is an antibiotic which can be detected by an innovative gas pressure-based biosensing platform.^{115, 116} A polyaniline nanowire functionalized reduced graphene oxide (PANI / rGO) framework was used as a CAT-like nanozyme that catalyzed the reduction of hydrogen peroxide to produce oxygen. The existence of kanamycin triggered strand displacement amplification which affected the CAT nanozyme and reflected the presence of kanamycin as an electrical signal which increased with increasing kanamycin concentration.^{115, 116}

Fig. 5 Different forms of nanozymes and their applications in environmental biotechnology (C-dots: carbon dots, NPs: nanoparticles, CAT-NP: catalytic nanoparticles, GQD: Graphene quantum dot, *E.coli*: *Escherichia coli*, *S.aureus*: *Staphylococcus aureus*, NPE-10: nonylphenyl poly (oxyethylene) ethers, VOCs: volatile organic compounds) (adapted from refs. 72, 133-141,149-160).

Ochratoxin is a mycotoxin that has attracted worldwide attention. It is one of a group of important, food-contaminating mycotoxins produced by seven species of *Aspergillus* and six species of *Penicillium*, four of which are the most toxic and widely distributed in the agricultural products. The most widely polluting and damaging to human health is ochratoxin A (OTA). One detection method was based on the biotin-streptavidin reaction.^{117, 118} Here, 3, 3', 5, 5'-tetramethylbenzidine (TMB) was

used as a substrate and a colorimetric reagent, and MnO₂ nanosheets were used as an OXD nanozyme to oxidize TMB to a blue colour TMB Ox. However, when OTA was present, acid-2-phosphate was converted to ascorbic acid, which reduced the MnO₂ nanosheet to Mn²⁺ which cannot oxidize TMB. This method for detecting OTA possessed high sensitivity, with a limit of detection being 0.069 nM.^{117, 118}

3. Application of nanozymes in environmental treatment

3.1 Nanozymes as antimicrobial and antifouling agents

Environmental antibiotic resistance is a rapidly increasing problem in recent years. Abuse of antibiotics can lead to the emergence of multi-drug resistant bacteria as well as causing environment pollution. Therefore, it is important to develop new antimicrobial agents that are highly effective, environmentally-friendly and which avoid or minimize drug resistance. Effects of antibacterial nanomaterials are multifaceted, which can make it difficult for bacteria to develop drug resistance. Compared with traditional nanomaterials, nanozymes have possess higher biosafety and show promise as an effective antibacterial material.^{119, 120}

Reactive oxygen species (ROS) play an important role in cellular defence against pathogen invasion^{121, 122}, and nanozymes have the ability to regulate level of ROS free radicals.¹²³ This ability confers an antibacterial function. For instance, hydrogen peroxide is a commonly used disinfectant because it can be decomposed to generate free radicals, thereby attacking cellular components of bacteria, such as membranes, proteins and nucleic acids.^{124, 125} However, the efficiency of generating free radicals is low, and the addition of a catalyst greatly accelerates the reaction. Nanomaterials with POD mimicking enzyme activity can be used as such a catalyst to improve the transformation of hydrogen peroxide to free hydroxy radicals and thus enhance sterilization.¹²⁶⁻¹²⁹ It was found that in the

presence of low concentrations of hydrogen peroxide, trace amounts of nanozymes could kill 100% *Escherichia coli* (*E. coli*), while the sterilization efficiency of hydrogen peroxide alone was less than 15%.¹³⁰ This study also found that vanadium pentoxide nanowires with vanadium haloperoxidase activity effectively inhibited formation of biofilm. In the presence of hydrogen peroxide, this substance can oxidize bromide ions to produce hypobromous acid (HOBr) and singlet oxygen, which has strong antibacterial activity. Applying vanadium pentoxide nanowires to the surface of stainless steel inhibited microbial adhesion, thus effectively preventing the formation of biofilm, and therefore has potential in antifouling applications, e.g. for ship hulls.

Photocatalytic cooperation with nanozymes can kill bacteria very effectively.^{131, 132} POD activity of a MoS₂ nanozyme was activated by lowering the pH which altered the surface charge of MoS₂ from negative to positive. The activated MoS₂ nanozyme catalyzed the decomposition of H₂O₂, and the resulting •OH destroyed cell integrity to achieve an antibacterial effect. The advantage of this method is that this antibacterial treatment can be accomplished simply by controlling the light.¹³³ Light-driven carbon dots (C-dots) were used as OXD nanozymes to kill *E. coli* and *S. aureus* by photosensitization, both ambient light and UV irradiation being tested.¹³⁴

Ultra-thin graphite carbon nitride (g-C₃N₄) AuNPs can be used as POD to efficiently catalyze the decomposition of H₂O₂ into •OH to kill drug-resistant Gram-negative and Gram-positive bacteria. This method was also very effective in destroying and preventing biofilm regeneration.¹²³ Catalytic nanoparticles containing biocompatible Fe₃O₄ and dextran coated iron oxide NPs also have POD activity and can be used to decompose H₂O₂ to produce •OH. This method degrades the biofilm matrix and kills bacteria quickly.^{135, 136}

Nano-CuO, as an artificial POD, is another kind of antibacterial material.¹³⁷ Nanozyme based

hydrogel (nanozyme-gel) CuO NPs and CuO nanorods (NRs) can be used to catalyze the decomposition of H_2O_2 to kill *E. coli*. Interestingly, the catalytic activity of CuO NRs showed significant catalytic enhancement under visible light irradiation, allowing light control of antibacterial activity.^{138, 139}

Nanoceria has a variety of enzymic properties. A nanoceria was discovered with both CAT and SOD properties, which was controlled by the $\text{Ce}^{3+}/\text{Ce}^{4+}$ ratio.¹⁴⁰ When the $\text{Ce}^{3+}/\text{Ce}^{4+}$ ratio and its activity are regulated, the cerium oxide nanozyme converts between these two properties. The superoxide anion is converted to H_2O_2 like SOD which is then further converted to H_2O and O_2 like CAT, and was effective in killing *E. coli* and *S. aureus*. CeO_{2-x} nanorods can somehow prevent biofouling in an aqueous environment because of haloperoxidase activity. One CeO_{2-x} NRs is stable in water, including marine environments, and can reduce bacteria adhesion by 70% compared to conventional PVA fibres.^{96-99, 141, 142}

Graphene quantum dots (GQD) also have multiple enzymatic properties like nanoceria. GQD can exhibit POD properties, e.g. addition of GQD can significantly improve the antibacterial activity of H_2O_2 , while GQD/AgNP hybrids can express an OXD function.^{72, 143}

Fig.6 Schematic of viral lipid peroxidation by IONzymes for virus inactivation. IONzymes directly contact with IAVs particles and collapses the viral lipid envelope by enhancing the level of lipid peroxidation, which further produces free radicals to destroy neighbouring proteins, including haemagglutinin, neuraminidase, and matrix protein 1, and impaires various viral structures and functions resulting in failed infection. (IONzymes: iron oxide nanozymes, IAVs: inactivated A viruses) (reproduced with permission from ref. 144, Copyright 2019, Ivyspring International Publisher) .

Most recently, iron oxide nanozymes (IONzymes) have been demonstrated to effectively inactivate A viruses (IAVs) by inducing envelope lipid peroxidation and destruction of the integrity of neighbouring proteins, including haemagglutinin, neuraminidase, and matrix protein 1 (Fig. 6). Furthermore, IONzymes possess broad-spectrum antiviral activity against 12 subtypes of IAVs (H1~H12).¹⁴⁴

3.2 Treatment of organic pollutants in water

Nanozymes have shown excellent qualities for the treatment of contaminated wastewater because they (i) can treat compounds that are normally difficult to biodegrade, (ii) can operate independently of the contaminant concentration, (iii) can operate over a wide range of pH, temperature and salinities, (iv) are not subject to inhibition from biofouling, (v) are relatively simple and easy to control, and (vi) possess high stability and are recyclable.¹⁴⁵⁻¹⁴⁸

Ferromagnetic chitosan nanozymes (MNP@CTS) has been synthesized which are more catalytically active than conventional ferromagnetic nanozymes for the degradation of phenol.¹⁴⁹ This type of nanozyme has excellent POD activity and can be prepared and regenerated easily at a lower cost than conventional horseradish peroxidase (HRP). MNP@CTS removed over 95% phenol from an aqueous solution within 5 h under the optimum conditions (pH range 2-10). What is more important is that the MNP@CTS are very stable and could be regenerated for reuse for at least ten cycles. In otherwork Mn(III)-chelate arising from manganese POD was pumped into a reaction vessel containing organic contaminants.¹⁵⁰ It was found that the Mn(III)-chelate efficiently oxidized 2, 4-dichlorophenol and 2, 4, 6-trichlorophenol. The Mn(III) was oxidized to Mn(III) at an initial rate of 78% under optimized conditions. This nanozyme had the advantage of retaining 88% of the initial MnP nanozyme activity after about 24 hours of continuous operation.

Aromatic compounds are a class of compounds possessing benzene ring structures. They are normally structurally stable, resistant to degradation, and often highly toxic, causing serious pollution to the environment and injurious to human health.^{151, 152} Lignin peroxidase (LiP) from a variety of sources can degrade a variety of recalcitrant aromatic compounds including polycyclic aromatic and phenolic compounds. In addition to exhibiting the normal properties of POD, the enzyme can form a

substrate cation radical with non-phenolic aromatic compounds and catalyze high-potential one-electron oxidation.^{153, 154}

Dyes are still a major problem in water pollution.^{155, 156} A new thermal-decomposition method was used to prepare ZnO nanorods and ZnO/CuO nanocomposites with different weight ratios (the maximum efficiency was observed for 5% CuO loaded on ZnO).¹⁵⁷ Organic dyes such as methylene blue and methyl orange were photocatalytically degraded by addition of composite catalyst under visible light irradiation. Preparation of this nanozyme is simple, rapid and economical.

Fig. 7 Photography image represents change in colour of textile dyes using ZnO/CuO (95:5) catalyst for different exposure time under visible light irradiation.) (adapted from refs. 157).

In other research, Au/TiO₂ powder was prepared by a sol-gel method, and this could photocatalytically degrade nonylphenyl poly (oxyethylene) ethers (NPE-10) under sunlight illumination.¹⁵⁸ The degradation rate of NPE-10 after irradiation for 4h was 91.8%, while that of TiO₂-P-25% and undoped TiO₂ was 66% and 52.6%, respectively.

3.3 Treatment of indoor air pollution

Nano-ecological-enzyme air purification material, another kind of nanozyme, is a new type of functional material with high purification efficiency, low wind resistance and sterilizable. It can be used

in air purifiers to remove indoor dust, microorganisms, formaldehyde and other volatile organic pollutants. The material is made of activated carbon fibre (ACF) and porous polymer composites and loaded with nano-silver and eco-enzyme catalyst.^{159, 160} Eco-enzymatic catalysts are supported in the nanoporous carbon structure and become composite macromolecules with active oxygen carriers. Enzymatic catalysts in the nanopores combine with oxygen to form highly active superoxide ions and oxidation-reduction active sub-fields, similar to POD that are widely distributed in nature. The contact area between the eco-enzyme catalyst and adsorbed formaldehyde in the nanopores is very large. The active catalyst molecule quickly binds the formaldehyde molecule and, after a series of oxidation-reductase catalytic reactions, different intermediate peroxide molecules are formed. Finally, the formaldehyde is oxidized to water and carbon dioxide. The eco-enzyme catalyst quickly returns to its original state and can bind again to oxygen molecule in the atmosphere. This process of enzymatic oxidation-reduction can therefore be repeated multiple times (Fig. 8). Organic molecules such as formaldehyde and microbial propagules in the air can be absorbed by the nanopores through an autonomous cycle and thus maintain the long-term purification effect of the composite material. The average purification rate of formaldehyde in two hours is 91.9%.^{159, 160}

Fig. 8 Degradation of formaldehyde in air by nano-ecological-enzymes (adapted from ref.159).

4. Conclusions and research prospects

In the past 10 years, nanozyme research has been carried out in more than 220 laboratories in 26 countries (Fig. 7), and nanozyme applications have also extended to biology, medicine, agriculture, environmental protection and other fields.³⁶ In the field of environmental biotechnology, nanozymes have multi-functional applications ranging from pollutant detection to treatment. Nanozymes can not only achieve the specificity and efficiency of natural enzymes, but of function independently of various environmental factors that may affect biotic systems, e.g. extremes of temperature and pH.

Fig. 9 The number of published papers on nanozymes has annually risen (source of data in the table: Google Scholar, December 31, 2018)

(adapted from ref.36).

Nanozymes also have several limitations, although nanozymes overcome many restrictive factors active against natural enzymes, most catalytic activities of nanozymes are still much lower than the corresponding natural enzymes. At present, research on nanozymes mainly concentrates on redox enzyme mimics, such as OXD, POD, CAT and SOD, with much less attention given to other enzymes that may be important in the degradation of some polymers. In addition, although the efficiency of

pollutant treatment is high, the cost of industrial treatment can be higher than traditional pollution treatment methods.

It is evident that nanozymes show good performance in small-scale experiments, but their application in environmental engineering is still limited, mainly because catalytic nanozyme devices require high precision technology, and an extended service life if such shortcomings can be overcome, applications of nanozymes for pollutant treatment industry may bring huge benefits. In addition, nanozymes can be combined with a variety of composite materials that allow application to changing environmental problems, which is also a challenging topic.^{161, 162}

Although current research on nanozymes is still limited, the future of nanozyme technology seems promising. In the field of environmental biotechnology, research on nanomaterials is increasing and new nanozymes continue to emerge significant research questions include how to effectively kill bacteria under adverse conditions, and how to degrade very recalcitrant organic polymers. Integration of nanozyme technology in the fields of environment, biology, agriculture and medicine could result in multi-level benefits for industrial development and human health.

References

1. U. Bornscheuer, G. Huisman, R. J. Kazlauskas, S. Lutz, J. Moore and K. Robins, Engineering the third wave of biocatalysis, *Nature*, 2012, **485**, 185.
2. K.-E. Jaeger and T. Eggert, Enantioselective biocatalysis optimized by directed evolution, *Current Opinion in Biotechnology*, 2004, **15**, 305-313.
3. J.-P. Genet, Asymmetric catalytic hydrogenation. Design of new Ru catalysts and chiral ligands: from laboratory to industrial applications, *Accounts of chemical research*, 2003, **36**,

344 908-918.

345 4. M. Behrens, F. Studt, I. Kasatkin, S. Kühl, M. Hävecker, F. Abild-Pedersen, S. Zander, F.

346 Girsdsies, P. Kurr and B.-L. Kniep, The active site of methanol synthesis over Cu/ZnO/Al₂O₃

347 industrial catalysts, *Science*, 2012, **336**, 893-897.

348 5. B. Meunier, S. P. de Visser and S. Shaik, Mechanism of oxidation reactions catalyzed by

349 cytochrome P450 enzymes, *Chemical reviews*, 2004, **104**, 3947-3980.

350 6. D. R. Paul and L. M. Robeson, Polymer nanotechnology: nanocomposites, *Polymer*, 2008, **49**,

351 3187-3204.

352 7. C. Guozhong, *Nanostructures and nanomaterials: synthesis, properties and applications*,

353 World scientific, 2004.

354 8. L. L. Dugan, J. K. Gabrielsen, P. Y. Shan, T.-S. Lin and D. W. Choi, Buckminsterfullerenol

355 free radical scavengers reduce excitotoxic and apoptotic death of cultured cortical neurons,

356 *Neurobiology of disease*, 1996, **3**, 129-135.

357 9. L. L. Dugan, D. M. Turetsky, C. Du, D. Lobner, M. Wheeler, C. R. Almli, C. K.-F. Shen, T.-Y.

358 Luh, D. W. Choi and T.-S. Lin, Carboxyfullerenes as neuroprotective agents, *Proceedings of*

359 *the National Academy of Sciences*, 1997, **94**, 9434-9439.

360 10. L. Gao, J. Zhuang, L. Nie, J. Zhang, Y. Zhang, N. Gu, T. Wang, J. Feng, D. Yang and S. Perrett,

361 Intrinsic peroxidase-like activity of ferromagnetic nanoparticles, *Nature nanotechnology*, 2007,

362 **2**, 577.

363 11. J. M. Perez, Iron oxide nanoparticles: hidden talent, *Nature Nanotechnology*, 2007, **2**, 535.

364 12. A. Karakoti, S. Singh, J. M. Dowding, S. Seal and W. T. Self, Redox-active radical scavenging

365 nanomaterials, *Chemical Society Reviews*, 2010, **39**, 4422-4432.

- 366 13. J. Xie, X. Zhang, H. Wang, H. Zheng and Y. Huang, Analytical and environmental
367 applications of nanoparticles as enzyme mimetics, *TrAC Trends in Analytical Chemistry*, 2012,
368 **39**, 114-129.
- 369 14. H. Wei and E. Wang, Nanomaterials with enzyme-like characteristics (nanozymes):
370 next-generation artificial enzymes, *Chemical Society Reviews*, 2013, **42**, 6060-6093.
- 371 15. G. Li-Zeng and Y. Xi-Yun, Discovery and current application of nanozyme, *Progress in*
372 *Biochemistry and Biophysics*, 2013, **40**, 892-902.
- 373 16. W. He, W. Wamer, Q. Xia, J.-j. Yin and P. P. Fu, Enzyme-like activity of nanomaterials,
374 *Journal of Environmental Science and Health, Part C*, 2014, **32**, 186-211.
- 375 17. Y. Lin, J. Ren and X. Qu, Nano-gold as artificial enzymes: hidden talents, *Advanced materials*,
376 2014, **26**, 4200-4217.
- 377 18. Y. Lin, J. Ren and X. Qu, Catalytically active nanomaterials: a promising candidate for
378 artificial enzymes, *Accounts of chemical research*, 2014, **47**, 1097-1105.
- 379 19. L. J. Prins, Emergence of complex chemistry on an organic monolayer, *Accounts of chemical*
380 *research*, 2015, **48**, 1920-1928.
- 381 20. L. Zheng, J. Zhao, X. Niu and Y. Yang, Nanomaterial-based peroxidase enzyme mimics with
382 applications to colorimetric analysis and electrochemical sensor, *Materials Review*, 2015, **29**,
383 129.
- 384 21. X. Wang, Y. Hu and H. Wei, Nanozymes in bionanotechnology: from sensing to therapeutics
385 and beyond, *Inorganic Chemistry Frontiers*, 2016, **3**, 41-60.
- 386 22. L. Gao and X. Yan, Nanozymes: an emerging field bridging nanotechnology and biology, *Sci*
387 *China Life Sci*, 2016, **59**, 400-402.

- 388 23. R. Ragg, M. N. Tahir and W. Tremel, Solids go bio: inorganic nanoparticles as enzyme mimics,
389 *European Journal of Inorganic Chemistry*, 2016, **2016**, 1906-1915.
- 390 24. E. Kuah, S. Toh, J. Yee, Q. Ma and Z. Gao, Enzyme mimics: advances and applications,
391 *Chemistry–A European Journal*, 2016, **22**, 8404-8430.
- 392 25. Q. Wang, H. Wei, Z. Zhang, E. Wang and S. Dong, Nanozyme: An emerging alternative to
393 natural enzyme for biosensing and immunoassay, *TrAC Trends in Analytical Chemistry*, 2018,
394 **105**, 218-224.
- 395 26. L. Pasquato, P. Pengo and P. Scrimin, Nanozymes: Functional nanoparticle-based catalysts,
396 *Supramolecular Chemistry*, 2005, **17**, 163-171.
- 397 27. Y. Xi-Yun, Nanozyme: a new type of artificial enzyme. *Journal*, 2018.
- 398 28. P. Weerathunge, R. Ramanathan, R. Shukla, T. K. Sharma and V. Bansal, Aptamer-controlled
399 reversible inhibition of gold nanozyme activity for pesticide sensing, *Analytical chemistry*,
400 2014, **86**, 11937-11941.
- 401 29. J. Golchin, K. Golchin, N. Alidadian, S. Ghaderi, S. Eslamkhah, M. Eslamkhah and A.
402 Akbarzadeh, Nanozyme applications in biology and medicine: an overview, *Artificial cells*,
403 *nanomedicine, and biotechnology*, 2017, **45**, 1069-1076.
- 404 30. D. Jiang, D. Ni, Z. T. Rosenkrans, P. Huang, X. Yan and W. Cai, Nanozyme: new horizons for
405 responsive biomedical applications, *Chemical Society Reviews*, 2019.
- 406 31. U. Wille and E. Juaristi, *Encyclopedia of Physical Organic Chemistry, 6 Volume Set*, John
407 Wiley & Sons, 2017.
- 408 32. D. Duan, K. Fan, D. Zhang, S. Tan, M. Liang, Y. Liu, J. Zhang, P. Zhang, W. Liu and X. Qiu,
409 Nanozyme-strip for rapid local diagnosis of Ebola, *Biosensors and Bioelectronics*, 2015, **74**,

410 134-141.

411 33. Y. Huang, J. Ren and X. Qu, Nanozymes: classification, catalytic mechanisms, activity
412 regulation, and applications, *Chemical reviews*, 2019.

413 34. J. Wu, X. Wang, Q. Wang, Z. Lou, S. Li, Y. Zhu, L. Qin and H. Wei, Nanomaterials with
414 enzyme-like characteristics (nanozymes): next-generation artificial enzymes (II), *Chemical*
415 *Society Reviews*, 2019, **48**, 1004-1076.

416 35. P. Rossi, F. Felluga, P. Tecilla, F. Formaggio, M. Crisma, C. Toniolo and P. Scrimin, An
417 azacrown-functionalized peptide as a metal ion based catalyst for the cleavage of a RNA-
418 model substrate, *Peptide Science*, 2000, **55**, 496-501.

419 36. Yan Xiyun, Nanozyme: a new generation of artificial enzyme, *Progress in Biochemistry and*
420 *Biophysics*, 2018, **45**, 101-104.(in Chinsese)

421 37. F. Natalio, R. André, A. F. Hartog, B. Stoll, K. P. Jochum, R. Wever and W. Tremel, Vanadium
422 pentoxide nanoparticles mimic vanadium haloperoxidases and thwart biofilm formation,
423 *Nature nanotechnology*, 2012, **7**, 530.

424 38. P. Biparva, S. M. Abedirad and S. Y. Kazemi, ZnO nanoparticles as an oxidase
425 mimic-mediated flow-injection chemiluminescence system for sensitive determination of
426 carvedilol, *Talanta*, 2014, **130**, 116-121.

427 39. C. Xu and X. Qu, Cerium oxide nanoparticle: a remarkably versatile rare earth nanomaterial
428 for biological applications, *NPG Asia Materials*, 2014, **6**, e90.

429 40. D. Yang, M. Fa, L. Gao, R. Zhao, Y. Luo and X. Yao, The effect of DNA on the oxidase
430 activity of nanoceria with different morphologies, *Nanotechnology*, 2018, **29**, 385101.

431 41. L. Huang, W. Zhang, K. Chen, W. Zhu, X. Liu, R. Wang, X. Zhang, N. Hu, Y. Suo and J.

432 Wang, Facet-selective response of trigger molecule to CeO₂ {1 1 0} for up-regulating
 433 oxidase-like activity, *Chemical Engineering Journal*, 2017, **330**, 746-752.

434 42. J. Liu, L. Meng, Z. Fei, P. J. Dyson, X. Jing and X. Liu, MnO₂ nanosheets as an artificial
 435 enzyme to mimic oxidase for rapid and sensitive detection of glutathione, *Biosensors and*
 436 *Bioelectronics*, 2017, **90**, 69-74.

437 43. X. Liu, Q. Wang, H. Zhao, L. Zhang, Y. Su and Y. Lv, BSA-templated MnO₂ nanoparticles as
 438 both peroxidase and oxidase mimics, *Analyst*, 2012, **137**, 4552-4558.

439 44. X. Yan, Y. Song, X. Wu, C. Zhu, X. Su, D. Du and Y. Lin, Oxidase-mimicking activity of
 440 ultrathin MnO₂ nanosheets in colorimetric assay of acetylcholinesterase activity, *Nanoscale*,
 441 2017, **9**, 2317-2323.

442 45. N. Singh, M. A. Savanur, S. Srivastava, P. D'Silva and G. Mugesh, A redox modulatory
 443 Mn₃O₄ nanozyme with multi-enzyme activity provides efficient cytoprotection to human cells
 444 in a Parkinson's disease model, *Angewandte Chemie International Edition*, 2017, **56**,
 445 14267-14271.

446 46. X. Zhang and Y. Huang, Evaluation of the antioxidant activity of phenols and tannic acid
 447 determination with Mn₃O₄ nano-octahedrons as an oxidase mimic, *Analytical Methods*,
 448 2015, **7**, 8640-8646.

449 47. H. Li, T. Wang, Y. Wang, S. Wang, P. Su and Y. Yang, Intrinsic triple-enzyme mimetic activity
 450 of V₆O₁₃ nanotextiles: mechanism investigation and colorimetric and fluorescent detections,
 451 *Industrial & Engineering Chemistry Research*, 2018, **57**, 2416-2425.

452 48. X. Zhang, S. He, Z. Chen and Y. Huang, CoFe₂O₄ nanoparticles as oxidase mimic-mediated
 453 chemiluminescence of aqueous luminol for sulfite in white wines, *Journal of agricultural and*

454 *food chemistry*, 2013, **61**, 840-847.

455 49. A. A. Vernekar, T. Das, S. Ghosh and G. Mugesh, A remarkably efficient MnFe₂O₄-based
 456 oxidase nanozyme, *Chemistry–An Asian Journal*, 2016, **11**, 72-76.

457 50. L. Su, W. Dong, C. Wu, Y. Gong, Y. Zhang, L. Li, G. Mao and S. Feng, The peroxidase and
 458 oxidase-like activity of NiCo₂O₄ mesoporous spheres: Mechanistic understanding and
 459 colorimetric biosensing, *Analytica chimica acta*, 2017, **951**, 124-132.

460 51. Y.-B. Feng, L. Hong, A.-L. Liu, W.-D. Chen, G.-W. Li, W. Chen and X.-H. Xia,
 461 High-efficiency catalytic degradation of phenol based on the peroxidase-like activity of cupric
 462 oxide nanoparticles, *International Journal of Environmental Science and Technology*, 2015,
 463 **12**, 653-660.

464 52. K. Korschelt, R. Schwidetzky, F. Pfitzner, J. Strugatchi, C. Schilling, M. von der Au, K.
 465 Kirchhoff, M. Panthöfer, I. Lieberwirth and M. Tahir, CeO_{2-x} nanorods with intrinsic
 466 urease-like activity, *Nanoscale*, 2018, **10**, 13074-13082.

467 53. J. Fan, J.-J. Yin, B. Ning, X. Wu, Y. Hu, M. Ferrari, G. J. Anderson, J. Wei, Y. Zhao and G.
 468 Nie, Direct evidence for catalase and peroxidase activities of ferritin–platinum nanoparticles,
 469 *Biomaterials*, 2011, **32**, 1611-1618.

470 54. X. Shen, W. Liu, X. Gao, Z. Lu, X. Wu and X. Gao, Mechanisms of oxidase and superoxide
 471 dismutation-like activities of gold, silver, platinum, and palladium, and their alloys: A general
 472 way to the activation of molecular oxygen, *Journal of the American Chemical Society*, 2015,
 473 **137**, 15882-15891.

474 55. G.-L. Wang, L.-Y. Jin, X.-M. Wu, Y.-M. Dong and Z.-J. Li, Label-free colorimetric sensor for
 475 mercury (II) and DNA on the basis of mercury (II) switched-on the oxidase-mimicking

activity of silver nanoclusters, *Analytica chimica acta*, 2015, **871**, 1-8.

56. C.-J. Yu, T.-H. Chen, J.-Y. Jiang and W.-L. Tseng, Lysozyme-directed synthesis of platinum nanoclusters as a mimic oxidase, *Nanoscale*, 2014, **6**, 9618-9624.

57. M. Cui, Y. Zhao, C. Wang and Q. Song, The oxidase-like activity of iridium nanoparticles, and their application to colorimetric determination of dissolved oxygen, *Microchimica Acta*, 2017, **184**, 3113-3119.

58. G.-J. Cao, X. Jiang, H. Zhang, T. R. Croley and J.-J. Yin, Mimicking horseradish peroxidase and oxidase using ruthenium nanomaterials, *RSC Advances*, 2017, **7**, 52210-52217.

59. G.-L. Wang, L.-Y. Jin, Y.-M. Dong, X.-M. Wu and Z.-J. Li, Intrinsic enzyme mimicking activity of gold nanoclusters upon visible light triggering and its application for colorimetric trypsin detection, *Biosensors and Bioelectronics*, 2015, **64**, 523-529.

60. M. Deng, S. Xu and F. Chen, Enhanced chemiluminescence of the luminol-hydrogen peroxide system by BSA-stabilized Au nanoclusters as a peroxidase mimic and its application, *Analytical Methods*, 2014, **6**, 3117-3123.

61. Y. Jv, B. Li and R. Cao, Positively-charged gold nanoparticles as peroxidase mimic and their application in hydrogen peroxide and glucose detection, *Chemical communications*, 2010, **46**, 8017-8019.

62. H. Jiang, Z. Chen, H. Cao and Y. Huang, Peroxidase-like activity of chitosan stabilized silver nanoparticles for visual and colorimetric detection of glucose, *Analyst*, 2012, **137**, 5560-5564.

63. L. Jin, Z. Meng, Y. Zhang, S. Cai, Z. Zhang, C. Li, L. Shang and Y. Shen, Ultrasmall Pt nanoclusters as robust peroxidase mimics for colorimetric detection of glucose in human serum, *ACS applied materials & interfaces*, 2017, **9**, 10027-10033.

498 64. Z. Gao, M. Xu, L. Hou, G. Chen and D. Tang, Irregular-shaped platinum nanoparticles as
 499 peroxidase mimics for highly efficient colorimetric immunoassay, *Analytica chimica acta*,
 500 2013, **776**, 79-86.

501 65. J. Lan, W. Xu, Q. Wan, X. Zhang, J. Lin, J. Chen and J. Chen, Colorimetric determination of
 502 sarcosine in urine samples of prostatic carcinoma by mimic enzyme palladium nanoparticles,
 503 *Analytica chimica acta*, 2014, **825**, 63-68.

504 66. L. Hu, Y. Yuan, L. Zhang, J. Zhao, S. Majeed and G. Xu, Copper nanoclusters as peroxidase
 505 mimetics and their applications to H₂O₂ and glucose detection, *Analytica chimica acta*, 2013,
 506 **762**, 83-86.

507 67. W. Huang, H. Wu, X. Li and T. Chen, Facile One-Pot Synthesis of Tellurium Nanorods as
 508 Antioxidant and Anticancer Agents, *Chemistry–An Asian Journal*, 2016, **11**, 2301-2311.

509 68. F. Wang, E. Ju, Y. Guan, J. Ren and X. Qu, Light-Mediated Reversible Modulation of ROS
 510 Level in Living Cells by Using an Activity-Controllable Nanozyme, *Small*, 2017, **13**,
 511 1603051.

512 69. W. He, Y.-T. Zhou, W. G. Wamer, M. D. Boudreau and J.-J. Yin, Mechanisms of the pH
 513 dependent generation of hydroxyl radicals and oxygen induced by Ag nanoparticles,
 514 *Biomaterials*, 2012, **33**, 7547-7555.

515 70. J. Gao, B. Jiang, C. Ni, Y. Qi and X. Bi, Enhanced reduction of nitrate by noble metal-free
 516 electrocatalysis on P doped three-dimensional Co₃O₄ cathode: Mechanism exploration from
 517 both experimental and DFT studies, *Chemical Engineering Journal*, 2019, 123034.

518 71. J. Gao, B. Jiang, C. Ni, Y. Qi, Y. Zhang, N. Oturan and M. A. Oturan, Non-precious
 519 Co₃O₄-TiO₂/Ti cathode based electrocatalytic nitrate reduction: Preparation, performance and

mechanism, *Applied Catalysis B: Environmental*, 2019, **254**, 391-402.

72. S. Chen, Y. Quan, Y.-L. Yu and J.-H. Wang, Graphene quantum dot/silver nanoparticle hybrids with oxidase activities for antibacterial application, *ACS Biomaterials Science & Engineering*, 2017, **3**, 313-321.

73. J. Wang, P. Su, D. Li, T. Wang and Y. Yang, Fabrication of CeO₂/rGO nanocomposites with oxidase-like activity and their application in colorimetric sensing of ascorbic acid, *Chemical Research in Chinese Universities*, 2017, **33**, 540-545.

74. Y. Guo, Y. Tao, X. Ma, J. Jin, S. Wen, W. Ji, W. Song, B. Zhao and Y. Ozaki, A dual colorimetric and SERS detection of Hg²⁺ based on the stimulus of intrinsic oxidase-like catalytic activity of Ag-CoFe₂O₄/reduced graphene oxide nanocomposites, *Chemical Engineering Journal*, 2018, **350**, 120-130.

75. S. Zhang, H. Li, Z. Wang, J. Liu, H. Zhang, B. Wang and Z. Yang, A strongly coupled Au/Fe₃O₄/GO hybrid material with enhanced nanozyme activity for highly sensitive colorimetric detection, and rapid and efficient removal of Hg²⁺ in aqueous solutions, *Nanoscale*, 2015, **7**, 8495-8502.

76. M. Vázquez-González, W.-C. Liao, R. m. Cazelles, S. Wang, X. Yu, V. Gutkin and I. Willner, Mimicking horseradish peroxidase functions using Cu²⁺-modified carbon nitride nanoparticles or Cu²⁺-modified carbon dots as heterogeneous catalysts, *ACS nano*, 2017, **11**, 3247-3253.

77. Y.-l. Dong, H.-g. Zhang, Z. U. Rahman, L. Su, X.-j. Chen, J. Hu and X.-g. Chen, Graphene oxide-Fe₃O₄ magnetic nanocomposites with peroxidase-like activity for colorimetric detection of glucose, *Nanoscale*, 2012, **4**, 3969-3976.

- 542 78. G. Darabdhara, B. Sharma, M. R. Das, R. Boukherroub and S. Szunerits, Cu-Ag bimetallic
543 nanoparticles on reduced graphene oxide nanosheets as peroxidase mimic for glucose and
544 ascorbic acid detection, *Sensors and Actuators B: Chemical*, 2017, **238**, 842-851.
- 545 79. E. J. Toone, *Advances in enzymology and related areas of molecular biology: Protein*
546 *evolution*, John Wiley & Sons, 2010.
- 547 80. M. Comotti, C. Della Pina, R. Matarrese and M. Rossi, The catalytic activity of “naked” gold
548 particles, *Angewandte Chemie International Edition*, 2004, **43**, 5812-5815.
- 549 81. I. V. Delidovich, B. L. Moroz, O. P. Taran, N. V. Gromov, P. A. Pyrjaev, I. P. Prosvirin, V. I.
550 Bukhtiyarov and V. N. Parmon, Aerobic selective oxidation of glucose to gluconate catalyzed
551 by Au/Al₂O₃ and Au/C: impact of the mass-transfer processes on the overall kinetics,
552 *Chemical engineering journal*, 2013, **223**, 921-931.
- 553 82. C. Ma, W. Xue, J. Li, W. Xing and Z. Hao, Mesoporous carbon-confined Au catalysts with
554 superior activity for selective oxidation of glucose to gluconic acid, *Green Chemistry*, 2013,
555 **15**, 1035-1041.
- 556 83. P. J. Miedziak, H. Alshammari, S. A. Kondrat, T. J. Clarke, T. E. Davies, M. Morad, D. J.
557 Morgan, D. J. Willock, D. W. Knight and S. H. Taylor, Base-free glucose oxidation using air
558 with supported gold catalysts, *Green Chemistry*, 2014, **16**, 3132-3141.
- 559 84. K. Odrozek, K. Maresz, A. Koreniuk, K. Prusik and J. Mrowiec-Białoń, Amine-stabilized
560 small gold nanoparticles supported on AISBA-15 as effective catalysts for aerobic glucose
561 oxidation, *Applied Catalysis A: General*, 2014, **475**, 203-210.
- 562 85. Y. Wang, S. Van de Vyver, K. K. Sharma and Y. Román-Leshkov, Insights into the stability of
563 gold nanoparticles supported on metal oxides for the base-free oxidation of glucose to

- 564 gluconic acid, *Green Chemistry*, 2014, **16**, 719-726.
- 565 86. M. Comotti, C. Della Pina, E. Falletta and M. Rossi, Aerobic oxidation of glucose with gold
566 catalyst: hydrogen peroxide as intermediate and reagent, *Advanced Synthesis & Catalysis*,
567 2006, **348**, 313-316.
- 568 87. H. Liang, F. Lin, Z. Zhang, B. Liu, S. Jiang, Q. Yuan and J. Liu, Multicopper laccase
569 mimicking nanozymes with nucleotides as ligands, *ACS applied materials & interfaces*, 2017,
570 **9**, 1352-1360.
- 571 88. M. Chen, Z. Wang, J. Shu, X. Jiang, W. Wang, Z.-H. Shi and Y.-W. Lin, Mimicking a natural
572 enzyme system: cytochrome c oxidase-like activity of Cu₂O nanoparticles by receiving
573 electrons from cytochrome c, *Inorganic chemistry*, 2017, **56**, 9400-9403.
- 574 89. F. Passardi, G. Theiler, M. Zamocky, C. Cosio, N. Rouhier, F. Teixeira, M. Margis-Pinheiro, V.
575 Ioannidis, C. Penel and L. Falquet, PeroxiBase: the peroxidase database, *Phytochemistry*,
576 2007, **68**, 1605-1611.
- 577 90. H. Wei and E. Wang, Fe₃O₄ magnetic nanoparticles as peroxidase mimetics and their
578 applications in H₂O₂ and glucose detection, *Analytical Chemistry*, 2008, **80**, 2250-2254.
- 579 91. R. Cheng, G.-q. Li, C. Cheng, L. Shi, X. Zheng and Z. Ma, Catalytic oxidation of
580 4-chlorophenol with magnetic Fe₃O₄ nanoparticles: mechanisms and particle transformation,
581 *RSC Advances*, 2015, **5**, 66927-66933.
- 582 92. Y.-h. Wu, L. Chu, W. Liu, L. Jiang, X.-y. Chen, Y.-h. Wang and Y.-l. Zhao, The screening of
583 metal ion inhibitors for glucose oxidase based on the peroxidase-like activity of nano-Fe₃O₄,
584 *RSC Advances*, 2017, **7**, 47309-47315.
- 585 93. A. Roy, R. Sahoo, C. Ray, S. Dutta and T. Pal, Soft template induced phase selective synthesis

586 of Fe₂O₃ nanomagnets: one step towards peroxidase-mimic activity allowing colorimetric
 587 sensing of thioglycolic acid, *RSC Advances*, 2016, **6**, 32308-32318.

588 94. M. Kluncker, M. Nawaz Tahir, R. Ragg, K. Korschelt, P. Simon, T. E. Gorelik, B. Barton, S. I.
 589 Shylin, M. Panthöfer and J. Herzberger, Pd@ Fe₂O₃ superparticles with enhanced peroxidase
 590 activity by solution phase epitaxial growth, *Chemistry of Materials*, 2017, **29**, 1134-1146.

591 95. T. Zhang, C. Cao, X. Tang, Y. Cai, C. Yang and Y. Pan, Enhanced peroxidase activity and
 592 tumour tissue visualization by cobalt-doped magnetoferritin nanoparticles, *Nanotechnology*,
 593 2016, **28**, 045704.

594 96. P. Chelikani, I. Fita and P. C. Loewen, Diversity of structures and properties among catalases,
 595 *Cellular and Molecular Life Sciences CMLS*, 2004, **61**, 192-208.

596 97. T. Pirmohamed, J. M. Dowding, S. Singh, B. Wasserman, E. Heckert, A. S. Karakoti, J. E.
 597 King, S. Seal and W. T. Self, Nanoceria exhibit redox state-dependent catalase mimetic
 598 activity, *Chemical communications*, 2010, **46**, 2736-2738.

599 98. I. Celardo, J. Z. Pedersen, E. Traversa and L. Ghibelli, Pharmacological potential of cerium
 600 oxide nanoparticles, *Nanoscale*, 2011, **3**, 1411-1420.

601 99. M. Hayyan, M. A. Hashim and I. M. AlNashef, Superoxide ion: generation and chemical
 602 implications, *Chemical reviews*, 2016, **116**, 3029-3085.

603 100. A. Okado-Matsumoto and I. Fridovich, Subcellular distribution of superoxide dismutases
 604 (SOD) in rat liver Cu, Zn-SOD in mitochondria, *Journal of Biological Chemistry*, 2001, **276**,
 605 38388-38393.

606 101. T. Yan, Q. Zhi-Yue, X. Zhuo-Bin and G. Li-Zeng, Antibacterial Mechanism and Applications
 607 of Nanozymes, *Progress in Biochemistry & Biophysics*, 2018, **45**, 118-128.

- 608 102. L. Järup, Hazards of heavy metal contamination, *British medical bulletin*, 2003, **68**, 167-182.
- 609 103. M. K. Raikwar, P. Kumar, M. Singh and A. Singh, Toxic effect of heavy metals in livestock
610 health, *Veterinary world*, 2008, **1**, 28.
- 611 104. J. Hu, Q. Zhuang, Y. Wang and Y. Ni, Label-free fluorescent catalytic biosensor for highly
612 sensitive and selective detection of the ferrous ion in water samples using a layered
613 molybdenum disulfide nanozyme coupled with an advanced chemometric model, *Analyst*,
614 2016, **141**, 1822-1829.
- 615 105. W. Li, G.-C. Fan, F. Gao, Y. Cui, W. Wang and X. Luo, High-activity Fe₃O₄ nanozyme as
616 signal amplifier: A simple, low-cost but efficient strategy for ultrasensitive
617 photoelectrochemical immunoassay, *Biosensors and Bioelectronics*, 2019, **127**, 64-71.
- 618 106. Z. Chen, C. Zhang, Q. Gao, G. Wang, L. Tan and Q. Liao, Colorimetric signal amplification
619 assay for mercury ions based on the catalysis of gold amalgam, *Analytical chemistry*, 2015, **87**,
620 10963-10968.
- 621 107. W. Li, B. Chen, H. Zhang, Y. Sun, J. Wang, J. Zhang and Y. Fu, BSA-stabilized Pt nanozyme
622 for peroxidase mimetics and its application on colorimetric detection of mercury (II) ions,
623 *Biosensors and Bioelectronics*, 2015, **66**, 251-258.
- 624 108. C.-W. Lien, B. Unnikrishnan, S. G. Harroun, C.-M. Wang, J.-Y. Chang, H.-T. Chang and C.-C.
625 Huang, Visual detection of cyanide ions by membrane-based nanozyme assay, *Biosensors and*
626 *Bioelectronics*, 2018, **102**, 510-517.
- 627 109. K. C. Jones and P. De Voogt, Persistent organic pollutants (POPs): state of the science,
628 *Environmental pollution*, 1999, **100**, 209-221.
- 629 110. F. Wania and D. Mackay, Peer reviewed: tracking the distribution of persistent organic

630 pollutants, *Environmental science & technology*, 1996, **30**, 390A-396A.

631 111. C. Comninellis, Electrocatalysis in the electrochemical conversion/combustion of organic
632 pollutants for waste water treatment, *Electrochimica Acta*, 1994, **39**, 1857-1862.

633 112. S. Singh, P. Tripathi, N. Kumar and S. Nara, Colorimetric sensing of malathion using
634 palladium-gold bimetallic nanozyme, *Biosensors and Bioelectronics*, 2017, **92**, 280-286.

635 113. N. Desneux, A. Decourtye and J.-M. Delpuech, The sublethal effects of pesticides on
636 beneficial arthropods, *Annu. Rev. Entomol.*, 2007, **52**, 81-106.

637 114. B. A. Croft, *Arthropod biological control agents and pesticides*, John Wiley and Sons Inc.,
638 1990.

639 115. R. Zeng, Z. Luo, L. Zhang and D. Tang, Platinum nanozyme-catalyzed gas generation for
640 pressure-based bioassay using polyaniline nanowires-functionalized graphene oxide
641 framework, *Analytical chemistry*, 2018, **90**, 12299-12306.

642 116. P. S. Stewart and J. W. Costerton, Antibiotic resistance of bacteria in biofilms, *The lancet*,
643 2001, **358**, 135-138.

644 117. F. Tian, J. Zhou, B. Jiao and Y. He, Nanozyme-based cascade colorimetric aptasensor for
645 amplified detection of ochratoxin A, *Nanoscale*, 2019.

646 118. K. Van der Merwe, P. Steyn, L. Fourie, D. B. Scott and J. Theron, Ochratoxin A, a toxic
647 metabolite produced by *Aspergillus ochraceus* Wilh, *Nature*, 1965, **205**, 1112.

648 119. A. P. Magiorakos, A. Srinivasan, R. Carey, Y. Carmeli, M. Falagas, C. Giske, S. Harbarth, J.
649 Hindler, G. Kahlmeter and B. Olsson-Liljequist, Multidrug-resistant, extensively drug-
650 resistant and pandrug-resistant bacteria: an international expert proposal for interim standard
651 definitions for acquired resistance, *Clinical microbiology and infection*, 2012, **18**, 268-281.

- 652 120. M. Rai, S. Deshmukh, A. Ingle and A. Gade, Silver nanoparticles: the powerful nanoweapon
653 against multidrug-resistant bacteria, *Journal of applied microbiology*, 2012, **112**, 841-852.
- 654 121. B. P. Yu, Cellular defenses against damage from reactive oxygen species, *Physiological*
655 *reviews*, 1994, **74**, 139-162.
- 656 122. S. Bhattacharya, in *Free radicals in human health and disease*, Springer, 2015, pp. 17-29.
- 657 123. Z. Wang, K. Dong, Z. Liu, Y. Zhang, Z. Chen, H. Sun, J. Ren and X. Qu, Activation of
658 biologically relevant levels of reactive oxygen species by Au/g-C₃N₄ hybrid nanozyme for
659 bacteria killing and wound disinfection, *Biomaterials*, 2017, **113**, 145-157.
- 660 124. E. Cabiscol Català, J. Tamarit Sumalla and J. Ros Salvador, Oxidative stress in bacteria and
661 protein damage by reactive oxygen species, *International Microbiology*, 2000, vol. 3, núm. 1,
662 p. 3-8, 2000.
- 663 125. O. Choi and Z. Hu, Size dependent and reactive oxygen species related nanosilver toxicity to
664 nitrifying bacteria, *Environmental science & technology*, 2008, **42**, 4583-4588.
- 665 126. K. Apel and H. Hirt, Reactive oxygen species: metabolism, oxidative stress, and signal
666 transduction, *Annu. Rev. Plant Biol.*, 2004, **55**, 373-399.
- 667 127. M. P. Murphy, How mitochondria produce reactive oxygen species, *Biochemical journal*, 2009,
668 **417**, 1-13.
- 669 128. M. L. Circu and T. Y. Aw, Reactive oxygen species, cellular redox systems, and apoptosis,
670 *Free Radical Biology and Medicine*, 2010, **48**, 749-762.
- 671 129. J. Nordberg and E. S. Arnér, Reactive oxygen species, antioxidants, and the mammalian
672 thioredoxin system, *Free radical biology and medicine*, 2001, **31**, 1287-1312.
- 673 130. K. Xu, D. Luan, X. Wang, B. Hu, X. Liu, F. Kong and B. Tang, An Ultrasensitive Cyclization-

674 Based Fluorescent Probe for Imaging Native HOBr in Live Cells and Zebrafish, *Angewandte*
675 *Chemie International Edition*, 2016, **55**, 12751-12754.

676 131. R. A. Damodar, S.-J. You and H.-H. Chou, Study the self cleaning, antibacterial and
677 photocatalytic properties of TiO₂ entrapped PVDF membranes, *Journal of hazardous*
678 *materials*, 2009, **172**, 1321-1328.

679 132. T. Paul, M. C. Dodd and T. J. Strathmann, Photolytic and photocatalytic decomposition of
680 aqueous ciprofloxacin: transformation products and residual antibacterial activity, *Water*
681 *research*, 2010, **44**, 3121-3132.

682 133. J. Niu, Y. Sun, F. Wang, C. Zhao, J. Ren and X. Qu, Photomodulated nanozyme used for a
683 Gram-selective antimicrobial, *Chemistry of Materials*, 2018, **30**, 7027-7033.

684 134. J. Zhang, X. Lu, D. Tang, S. Wu, X. Hou, J. Liu and P. Wu, Phosphorescent carbon dots for
685 highly efficient oxygen photosensitization and as photo-oxidative nanozymes, *ACS applied*
686 *materials & interfaces*, 2018, **10**, 40808-40814.

687 135. L. Gao, Y. Liu, D. Kim, Y. Li, G. Hwang, P. C. Naha, D. P. Cormode and H. Koo,
688 Nanocatalysts promote *Streptococcus mutans* biofilm matrix degradation and enhance
689 bacterial killing to suppress dental caries in vivo, *Biomaterials*, 2016, **101**, 272-284.

690 136. P. C. Naha, Y. Liu, G. Hwang, Y. Huang, S. Gubara, V. Jonnakuti, A. Simon-Soro, D. Kim, L.
691 Gao and H. Koo, Dextran-Coated Iron Oxide Nanoparticles as Biomimetic Catalysts for
692 Localized and pH-Activated Biofilm Disruption, *ACS nano*, 2019.

693 137. D. Das, B. C. Nath, P. Phukon and S. K. Dolui, Synthesis and evaluation of antioxidant and
694 antibacterial behavior of CuO nanoparticles, *Colloids and Surfaces B: Biointerfaces*, 2013,
695 **101**, 430-433.

696 138. Y. Ye, L. Xiao, B. He, Q. Zhang, T. Nie, X. Yang, D. Wu, H. Cheng, P. Li and Q. Wang,
697 Oxygen-tuned nanozyme polymerization for the preparation of hydrogels with printable and
698 antibacterial properties, *Journal of Materials Chemistry B*, 2017, **5**, 1518-1524.

699 139. M. N. Karim, M. Singh, P. Weerathunge, P. Bian, R. Zheng, C. Dekiwadia, T. Ahmed, S. Walia,
700 E. Della Gaspera and S. Singh, Visible-Light-Triggered Reactive-Oxygen-Species-Mediated
701 Antibacterial Activity of Peroxidase-Mimic CuO Nanorods, *ACS Applied Nano Materials*,
702 2018, **1**, 1694-1704.

703 140. M. T. Matter, L. A. Furer, F. H. Starsich, G. Fortunato, S. E. Pratsinis and I. K. Herrmann,
704 Engineering the Bioactivity of Flame-Made Ceria and Ceria/Bioglass Hybrid Nanoparticles,
705 *ACS applied materials & interfaces*, 2018, **11**, 2830-2839.

706 141. M. Hu, K. Korschelt, M. Viel, N. Wiesmann, M. Kappl, J. r. Brieger, K. Landfester, H.
707 Thérien-Aubin and W. Tremel, Nanozymes in Nanofibrous Mats with Haloperoxidase-like
708 Activity To Combat Biofouling, *ACS applied materials & interfaces*, 2018, **10**, 44722-44730.

709 142. Z.-Y. Yang, S.-L. Luo, H. Li, S.-W. Dong, J. He, H. Jiang, R. Li and X.-C. Yang, Alendronate
710 as a robust anchor for ceria nanoparticle surface coating: facile binding and improved
711 biological properties, *RSC Advances*, 2014, **4**, 59965-59969.

712 143. Z. Chen, Z. Wang, J. Ren and X. Qu, Enzyme mimicry for combating bacteria and biofilms,
713 *Accounts of chemical research*, 2018, **51**, 789-799.

714 144. T. Qin, R. Ma, Y. Yin, X. Miao, S. Chen, K. Fan, J. Xi, Q. Liu, Y. Gu and Y. Yin, Catalytic
715 inactivation of influenza virus by iron oxide nanozyme, *Theranostics*, 2019, **9**, 6920.

716 145. C. S. Turchi and D. F. Ollis, Photocatalytic degradation of organic water contaminants:
717 mechanisms involving hydroxyl radical attack, *Journal of catalysis*, 1990, **122**, 178-192.

- 718 146. R. J. Tayade, P. K. Surolia, R. G. Kulkarni and R. V. Jasra, Photocatalytic degradation of dyes
719 and organic contaminants in water using nanocrystalline anatase and rutile TiO₂, *Science and*
720 *Technology of Advanced Materials*, 2007, **8**, 455.
- 721 147. D. R. Lovley, Bioremediation of organic and metal contaminants with dissimilatory metal
722 reduction, *Journal of industrial microbiology*, 1995, **14**, 85-93.
- 723 148. L. N. Nguyen, F. I. Hai, W. E. Price, F. D. Leusch, F. Roddick, H. H. Ngo, W. Guo, S. F.
724 Magram and L. D. Nghiem, The effects of mediator and granular activated carbon addition on
725 degradation of trace organic contaminants by an enzymatic membrane reactor, *Bioresource*
726 *technology*, 2014, **167**, 169-177.
- 727 149. J. Jiang, C. He, S. Wang, H. Jiang, J. Li and L. Li, Recyclable ferromagnetic chitosan
728 nanozyme for decomposing phenol, *Carbohydrate polymers*, 2018, **198**, 348-353.
- 729 150. A. C. Grabski, H. J. Grimek and R. R. Burgess, Immobilization of manganese peroxidase from
730 *Lentinula edodes* and its biocatalytic generation of MnIII-chelate as a chemical oxidant of
731 chlorophenols, *Biotechnology and bioengineering*, 1998, **60**, 204-215.
- 732 151. M. Fujihira, Y. Satoh and T. Osa, Heterogeneous photocatalytic oxidation of aromatic
733 compounds on TiO₂, *Nature*, 1981, **293**, 206.
- 734 152. M. Blumer, Polycyclic aromatic compounds in nature, *Scientific American*, 1976, **234**, 34-45.
- 735 153. T. Johjima, N. Itoh, M. Kabuto, F. Tokimura, T. Nakagawa, H. Wariishi and H. Tanaka, Direct
736 interaction of lignin and lignin peroxidase from *Phanerochaete chrysosporium*, *Proceedings of*
737 *the National Academy of Sciences*, 1999, **96**, 1989-1994.
- 738 154. N. Duran and E. Esposito, Potential applications of oxidative enzymes and phenoloxidase-like
739 compounds in wastewater and soil treatment: a review, *Applied catalysis B: environmental*,

740 2000, **28**, 83-99.

741 155. B. Padhi, Pollution due to synthetic dyes toxicity & carcinogenicity studies and remediation,
742 *International Journal of Environmental Sciences*, 2012, **3**, 940.

743 156. Q. Zhou, Chemical pollution and transport of organic dyes in water–soil–crop systems of the
744 Chinese Coast, *Bulletin of environmental contamination and toxicology*, 2001, **66**, 784-793.

745 157. R. Saravanan, S. Karthikeyan, V. Gupta, G. Sekaran, V. Narayanan and A. Stephen, Enhanced
746 photocatalytic activity of ZnO/CuO nanocomposite for the degradation of textile dye on
747 visible light illumination, *Materials Science and Engineering: C*, 2013, **33**, 91-98.

748 158. Z. Du, C. Feng, Q. Li, Y. Zhao and X. Tai, Photodegradation of NPE-10 surfactant by
749 Au-doped nano-TiO₂, *Colloids and Surfaces A: Physicochemical and Engineering Aspects*,
750 2008, **315**, 254-258.

751 159. Yuqun Wang, Xiangyu Jia and Yunlong Zhang, Nanozyme air materials and their applications
752 in air purifiers, *Jiangsu Architecture*, 2005, **4**, 36-38. (in Chinese)

753 160. Zhang Qingsong, Wang Yuqun, Jia Xiangyi and Zhang Yunlong, Research on air purification
754 equipment of central air conditioning and ventilation system, *Jiangsu Architecture*, 2006, **6**,
755 73-76. (in Chinese)

756 161. Q. Wang, X. Zhang, L. Huang, Z. Zhang and S. Dong, One-pot synthesis of Fe₃O₄
757 nanoparticle loaded 3D porous graphene nanocomposites with enhanced nanozyme activity
758 for glucose detection, *ACS applied materials & interfaces*, 2017, **9**, 7465-7471.

759 162. S. Li, X. Liu, H. Chai and Y. Huang, Recent advances in the construction and analytical
760 applications of metal-organic frameworks-based nanozymes, *TrAC Trends in Analytical*
761 *Chemistry*, 2018, **105**, 391-403.