



University of Dundee

Iron coral

Li, Qianwei; Liu, Daoqing; Wang, Tongzhe; Chen, Chunmao; Gadd, Geoffrey Michael

Published in:
Chemical Engineering Journal

DOI:
[10.1016/j.cej.2020.126263](https://doi.org/10.1016/j.cej.2020.126263)

Publication date:
2020

Document Version
Peer reviewed version

[Link to publication in Discovery Research Portal](#)

Citation for published version (APA):

Li, Q., Liu, D., Wang, T., Chen, C., & Gadd, G. M. (2020). Iron coral: Novel fungal biomineralization of nanoscale zerovalent iron composites for treatment of chlorinated pollutants. *Chemical Engineering Journal*, 402, Article 126263. <https://doi.org/10.1016/j.cej.2020.126263>

General rights

Copyright and moral rights for the publications made accessible in Discovery Research Portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Supporting Information

Iron coral: novel fungal biomineralization of nanoscale zerovalent iron composites for treatment of chlorinated pollutants

Qianwei Li^{1,†}, Daoqing Liu^{2,3,†}, Tongzhe Wang¹, Chunmao Chen^{1}, and Geoffrey Michael Gadd^{1,4}*

¹State Key Laboratory of Heavy Oil Processing, State Key Laboratory of Petroleum Pollution Control, China University of Petroleum-Beijing, Beijing 102249, China

²Department of Environmental Engineering, Peking University, Beijing 100871, China

³The Key Laboratory of Water and Sediment Sciences, Ministry of Education, Beijing 100871, China

⁴Geomicrobiology Group, School of Life Sciences, University of Dundee, Dundee DD1 5EH, Scotland, UK

*Corresponding author: Chunmao Chen, State Key Laboratory of Heavy Oil Processing, State Key Laboratory of Petroleum Pollution Control, China University of Petroleum-Beijing, Beijing 102249, China. (chunmaochan@163.com)

[†]Both authors contributed equally to this work.

Sample preparation for Tafel scanning

Tafel scans were performed using a CHI-660E electrochemical workstation fitted with a three-electrode system enabling the free corrosion potentials to be recorded. The working electrode was fabricated with glass carbon ($d = 3$ mm) to form a small cavity. 5 mg of iron coral composite was pressed into the cavity and 20 μ l of nafion solution was dropped on the composite to enhance attachment to the electrode. After drying at room temperature, the iron coral loaded electrode was immersed into NaSO₄ solution (0.5 mM) for electrochemical measurements.




Fig. S1 X-ray mapping of elements in ‘iron coral’ after biomass-FeCO₃ carbonization and reduction at 900°C for 1 h. (A) SEM image of Fe-containing minerals. EDXA confirmed the presence of three elements within the mineral (Fe, C and O) (scale bar = 20 μ m), (B) iron, (C) carbon and (D) oxygen. Typical images are shown from many similar samples.




Fig. S2 Pore characteristics of the carbonized fungal biomass and iron coral. (A) Nitrogen sorption isotherms and (B) pore size distributions. Typical data are shown from one of several determinations.




Fig. S3 Zeta potential of iron coral and commercial nZVI in aqueous solution. Typical data are shown from one of several determinations.